

# **OIL ANALYSIS REPORT**

#### Sample Rating Trend





## Component Diesel Engine Fluid DIESEL ENGINE OIL SAE 15W40 (--- GAL)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

#### Wear

All component wear rates are normal.

#### Contamination

Elevated aluminum (AI) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components. There is no indication of any contamination in the oil.


### Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

			Jan2023	0ct2023		
SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number Sample Date Machine Age Oil Age	hrs hrs	Client Info Client Info Client Info Client Info		WC0847970 19 Oct 2023 3539 1156	WC0759973 06 Jan 2023 2383 0	 
Oil Changed Sample Status		Client Info		Changed NORMAL	Changed NORMAL	
CONTAMINATION	1	method	limit/base	current	history1	history2
Fuel Water Glycol		WC Method WC Method WC Method	>5 >0.2	<1.0 NEG NEG	<1.0 NEG NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron Chromium	ppm ppm	ASTM D5185m ASTM D5185m	>100 >20	30 <1	34 <1	
Nickel Titanium	ppm ppm	ASTM D5185m ASTM D5185m	>4	0 <1	0 0	
Silver Aluminum Lead	ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	>3 >20 >40	0 88 <1	0 30 0	
Copper Tin	ppm ppm ppm	ASTM D5185m ASTM D5185m		<1 1 2	2 <1	
Vanadium Cadmium	ppm ppm	ASTM D5185m ASTM D5185m		<1 0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron Barium	ppm ppm	ASTM D5185m ASTM D5185m	250 10	7 0	3 <1	
Molybdenum Manganese Magnesium	ppm ppm ppm	ASTM D5185m ASTM D5185m ASTM D5185m	100 450	63 <1 889	58 <1 796	
Calcium Phosphorus	ppm ppm	ASTM D5185m ASTM D5185m	3000 1150	1118 940	1143 937	
Zinc Sulfur	ppm ppm	ASTM D5185m ASTM D5185m	1350 4250	1198 2879	1148 3040	
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon Sodium	ppm ppm	ASTM D5185m	>25 >158	7 4	6 2	
Potassium	ppm	ASTM D5185m		207	66	
INFRA-RED	%	method *ASTM D7844	limit/base	current 0.7	history1 0.6	history2
Nitration Sulfation	Abs/cm Abs/.1mm	*ASTM D7844 *ASTM D7624 *ASTM D7415	>3 >20 >30	0.7 10.0 20.9	9.9 20.8	
FLUID DEGRADA		method	limit/base	current	history1	history2
Oxidation Base Number (BN)	Abs/.1mm mg KOH/g	*ASTM D7414 ASTM D2896	>25 8.5	18.9 7.7	18.0 7.6	



# **OIL ANALYSIS REPORT**









Apple Valley Waste - Chambersburg Location 5436 Sunset Pike Chambersburg, PA US 17202 Contact: Service Manager

Test Package : CONST (Additional Tests: TBN) To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

: 16 Jan 2024

: 17 Jan 2024

: Wes Davis

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

: WC0847970

:06061848

: 10833230

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Diagnostician

Recieved

Diagnosed

Certificate L2367

Laboratory

Sample No.

Lab Number

Unique Number

Submitted By: BOB MCQUADE

Page 2 of 2

T: F: