

OIL ANALYSIS REPORT

KAESER ASD 25 5194770 (S/N 1047) Component

Compressor

KAESER SIGMA (OEM) M-460 (--- GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is a high amount of particulates present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KCPA009077	KCP46524D	KCP36577
Sample Date		Client Info		13 Dec 2023	14 Oct 2022	03 Sep 2021
Machine Age	hrs	Client Info		19565	18898	17424
Oil Age	hrs	Client Info		0	2000	1415
Oil Changed		Client Info		N/A	Changed	Changed
Sample Status				ABNORMAL	ABNORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1	<1	<1
Chromium	ppm	ASTM D5185m	>10	0	0	<1
Nickel	ppm	ASTM D5185m	>3	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m		1	<1	3
Lead	ppm	ASTM D5185m	>10	0	<1	0
Copper	ppm	ASTM D5185m		3	2	2
Tin	ppm		>10	0	0	0
Antimony	ppm	ASTM D5185m	-			<1
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
	1991II		11	-		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	<1
Barium	ppm	ASTM D5185m	90	0	0	0
Molybdenum	ppm	ASTM D5185m	0	0	0	0
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m	100	48	52	65
Calcium	ppm	ASTM D5185m		<1	0	0
Phosphorus	ppm	ASTM D5185m	0	12	3	3
Zinc	ppm	ASTM D5185m	0	0	24	33
Sulfur	ppm	ASTM D5185m	23500	19751	20615	17446
CONTAMINANTS	3	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	0	<1
Sodium	ppm	ASTM D5185m		20	20	23
Potassium	ppm	ASTM D5185m	>20	10	10	11
Water	%	ASTM D6304	>0.05	0.022	0.033	0.032
ppm Water	ppm	ASTM D6304	>500	224	339.8	327.3
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		39526	7930	2146
Particles >6µm		ASTM D7647	>1300	<u> </u>	A 2721	669
Particles >14µm		ASTM D7647	>80	653	A 233	55
Particles >21µm		ASTM D7647	>20	<u> </u>	6 1	12
Particles >38µm		ASTM D7647	>4	A 141	6	0
Particles >71µm		ASTM D7647	>3	<u> </u>	1	0
Oil Cleanliness		ISO 4406 (c)	>17/13	A 22/20	1 9/15	17/13
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.38	0.37	0.355
	0 - 0					


Contact/Location: MATT BADE - MELWAS



OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	45	44.0	45.7	46.6
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				a.		

Bottom

