




OIL ANALYSIS REPORT

Sample Rating Trend



ISO



Machine Id
KAESER AIRTOWER 7.5C 6693916 (S/N 1925)

Component
Compressor

Fluid
KAESER SIGMA (OEM) M-460 (--- GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Oil and filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a high amount of particulates present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

| | method | limit/base | current | history1 | history2 |
|---------------|-------------|-------------|--------------------|-------------|-------------|
| Sample Number | Client Info | | KCP41514 | KCP53361 | KCP41517 |
| Sample Date | Client Info | | 12 Jan 2024 | 30 Nov 2022 | 28 Jul 2021 |
| Machine Age | hrs | Client Info | 7095 | 4905 | 3735 |
| Oil Age | hrs | Client Info | 2500 | 1170 | 2300 |
| Oil Changed | Client Info | | Changed | Changed | Changed |
| Sample Status | | | ABNORMAL | NORMAL | ABNORMAL |

WEAR METALS

| | method | limit/base | current | history1 | history2 |
|----------|--------|-----------------|--------------|----------|----------|
| Iron | ppm | ASTM D5185m >50 | <1 | <1 | 1 |
| Chromium | ppm | ASTM D5185m >10 | 0 | <1 | <1 |
| Nickel | ppm | ASTM D5185m >3 | <1 | <1 | 1 |
| Titanium | ppm | ASTM D5185m >3 | 0 | 0 | 0 |
| Silver | ppm | ASTM D5185m >2 | 0 | 0 | <1 |
| Aluminum | ppm | ASTM D5185m >10 | 1 | <1 | 0 |
| Lead | ppm | ASTM D5185m >10 | 0 | 0 | <1 |
| Copper | ppm | ASTM D5185m >50 | 16 | 14 | 28 |
| Tin | ppm | ASTM D5185m >10 | 0 | <1 | <1 |
| Antimony | ppm | ASTM D5185m | --- | --- | 0 |
| Vanadium | ppm | ASTM D5185m | 0 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | 0 | 0 | 0 |

ADDITIVES

| | method | limit/base | current | history1 | history2 |
|------------|--------|-------------------|--------------|----------|----------|
| Boron | ppm | ASTM D5185m 0 | 0 | 0 | <1 |
| Barium | ppm | ASTM D5185m 90 | 0 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m 0 | 0 | 0 | 0 |
| Manganese | ppm | ASTM D5185m | 0 | <1 | <1 |
| Magnesium | ppm | ASTM D5185m 100 | 13 | 16 | 7 |
| Calcium | ppm | ASTM D5185m 0 | 0 | 0 | 0 |
| Phosphorus | ppm | ASTM D5185m 0 | 11 | 38 | 4 |
| Zinc | ppm | ASTM D5185m 0 | 2 | 28 | 2 |
| Sulfur | ppm | ASTM D5185m 23500 | 19451 | 22242 | 16314 |

CONTAMINANTS

| | method | limit/base | current | history1 | history2 |
|-----------|--------|------------------|--------------|----------|----------|
| Silicon | ppm | ASTM D5185m >25 | <1 | <1 | <1 |
| Sodium | ppm | ASTM D5185m | 3 | 7 | <1 |
| Potassium | ppm | ASTM D5185m >20 | <1 | 0 | <1 |
| Water | % | ASTM D6304 >0.05 | 0.010 | 0.010 | ▲ 0.388 |
| ppm Water | ppm | ASTM D6304 >500 | 104 | 106.9 | ▲ 3880 |






FLUID CLEANLINESS

| | method | limit/base | current | history1 | history2 |
|-----------------|--------------|------------|-------------------|----------|----------|
| Particles >4µm | ASTM D7647 | | 23239 | 4182 | --- |
| Particles >6µm | ASTM D7647 | >1300 | ▲ 8857 | 1267 | --- |
| Particles >14µm | ASTM D7647 | >80 | ▲ 694 | 52 | --- |
| Particles >21µm | ASTM D7647 | >20 | ▲ 142 | 9 | --- |
| Particles >38µm | ASTM D7647 | >4 | ▲ 5 | 1 | --- |
| Particles >71µm | ASTM D7647 | >3 | 1 | 0 | --- |
| Oil Cleanliness | ISO 4406 (c) | >--/17/13 | ▲ 22/20/17 | 19/17/13 | --- |

FLUID DEGRADATION

| | method | limit/base | current | history1 | history2 |
|------------------|----------|----------------|-------------|----------|----------|
| Acid Number (AN) | mg KOH/g | ASTM D8045 1.0 | 0.38 | 0.32 | 0.290 |

OIL ANALYSIS REPORT








| PARAMETER | method | limit/base | current | history1 | history2 |
|------------------|--------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | ▲ MODER |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.05 | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | ▲ 1.0 |

| FLUID PROPERTIES | method | limit/base | current | history1 | history2 |
|------------------|--------|--------------|---------|----------|----------|
| Visc @ 40°C | cSt | ASTM D445 45 | 51.2 | 48.0 | 45.2 |

| SAMPLE IMAGES | method | limit/base | current | history1 | history2 |
|---------------|--------|------------|---------|----------|----------|
| Color | | | | | |
| Bottom | | | | | |

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : KCP41514 **Recieved** : 16 Jan 2024
Lab Number : 06062007 **Diagnosed** : 18 Jan 2024
Unique Number : 10833389 **Diagnostician** : Don Baldrige
Test Package : IND 2 (Additional Tests: KF, PrtCount)

MARINE SYSTEM DESIGN
 106 STATON CT
 GREENVILLE, NC
 US 27834
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: