

Area MIXERS

**M-301** Component Gearbox Elui

## **OIL ANALYSIS REPORT**

Sample Rating Trend



		Jan2020 Ju	12020 Jan2021 Jul2021	Jan2022 Jul2022 Jan2023 Jul2	123 Jan 2024	
SAMPLE INFOR	RMATION	method	limit/base	current	history1	history
Sample Number		Client Info		WC0896653	WC0830811	WC077904
Sample Date		Client Info		12 Jan 2024	06 Jul 2023	17 Jan 202
Machine Age	mths	Client Info		23	23	1
Oil Age	mths	Client Info		23	23	1
Oil Changed		Client Info		N/A	Not Changd	Not Chang
Sample Status				NORMAL	NORMAL	ABNORMA
CONTAMINATIO	N	method	limit/base	current	history1	history
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history
Iron	ppm	ASTM D5185m	>200	8	9	12
Chromium	ppm	ASTM D5185m	>15	0	0	0
Nickel	ppm	ASTM D5185m	>15	0	0	0
Titanium	ppm	ASTM D5185m		0	<1	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m		1	<1	0
Lead	ppm	ASTM D5185m	>100	0	0	0
Copper	ppm	ASTM D5185m	>200	<1	0	<1
Tin	ppm	ASTM D5185m	>25	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m		<1	4	<1
Calcium	ppm	ASTM D5185m		<1	0	0
Phosphorus	ppm	ASTM D5185m		463	425	421
Zinc	ppm	ASTM D5185m		0	10	2
Sulfur	ppm	ASTM D5185m		20	42	57
CONTAMINANT		method	limit/base	current	history1	history
Silicon	ppm	ASTM D5185m	>50	42	38	42
Sodium	ppm	ASTM D5185m		<1	<1	0
Potassium	ppm	ASTM D5185m		<1	<1	<1
FLUID CLEANLI	NESS	method	limit/base	current	history1	history
Particles >4µm		ASTM D7647	>20000	16735		▲ 70861
Particles >6µm		ASTM D7647		843		2270
Particles >14µm		ASTM D7647	>640	50		52
Particles >21µm		ASTM D7647		15		9
Particles >38µm		ASTM D7647	>40	1		0
Particles >71µm		ASTM D7647		1		0
Oil Cleanliness		ISO 4406 (c)	>21/19/16	21/17/13		<b>A</b> 23/18/13
FLUID DEGRAD	ATION	method	limit/base	current	history1	history

Recommendation

MOBIL SHC 630 (12 GAL)

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

## Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

## Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

Report Id: POEGRO [WUSCAR] 06062621 (Generated: 01/19/2024 10:56:30) Rev: 1

Acid Number (AN)

mg KOH/g ASTM D8045


0.56 0.48


0.57


Submitted By: GAVIN KRUEGER



## **OIL ANALYSIS REPORT**







5 100

50

0


Jan 15/20

Abnorma


Jul28/20

Jan 12/21

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	217.7	219	220	219
SAMPLE IMAGES	6	method	limit/base	current	history1	history2
Color				•		



Bottom



Submitted By: GAVIN KRUEGER

Page 2 of 2