

### **OIL ANALYSIS REPORT**

Sample Rating Trend

NORMAL

# CINCINNATTI PRESS BRAKE

West Hydraulic System Fluid MOBIL DTE 24 (260 GAL)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear

All component wear rates are normal.


#### Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

#### Particle Filter (Magn: 200 x)







				Jan 2024		
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		PH0002818		
Sample Date		Client Info		02 Jan 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATION	J	method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	<1		
Chromium	ppm	ASTM D5185m	>20	0		
Nickel	ppm	ASTM D5185m	>20	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>20	1		
Lead	ppm	ASTM D5185m	>20	0		
Copper	ppm	ASTM D5185m	>20	<1		
Tin	ppm	ASTM D5185m	>20	0		
Vanadium	ppm	ASTM D5185m	0	0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		<1		
Calcium	ppm	ASTM D5185m		159		
Phosphorus	ppm	ASTM D5185m		511		
Zinc	ppm	ASTM D5185m		731		
Sulfur	ppm	ASTM D5185m		3069		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	3		
Sodium	ppm	ASTM D5185m		<1		
Potassium	ppm	ASTM D5185m	>20	<1		
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>10000	4318		
Particles >6µm		ASTM D7647	>2500	1230		
Particles >14µm		ASTM D7647	>320	109		
Particles >21µm		ASTM D7647	>80	26		
Particles >38µm		ASTM D7647	>20	1		
Particles >71µm		ASTM D7647	>4	0		
Oil Cleanliness		ISO 4406 (c)	>20/18/15	19/17/14		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		1.08		

Report Id: RAEPRYOK [WUSCAR] 06062644 (Generated: 01/23/2024 14:45:20) Rev: 1

Contact/Location: WEBCHECK IN RAEPRY - OTIS HOLT - RAEPRYOK



38 36 3 cSt (40°C) 25 (40°C) 30 Ab 28 26 Jan2/24

12


Ø

21 Ok Jan2/24

Particle Trend

2m ί4μm

## **OIL ANALYSIS REPORT**



т26	VISUAL		method	limit/base	current	history1	history2
-24	White Metal	scalar	*Visual	NONE	NONE		
-22 8	Yellow Metal	scalar	*Visual	NONE	NONE		
18 6	Precipitate	scalar	*Visual	NONE	NONE		
-20 4406:1999 Cleanliness -16 -14 -14 -12	Silt	scalar	*Visual	NONE	NONE		
-14	Debris	scalar	*Visual	NONE	NONE		
-12 s -10 de	Sand/Dirt	scalar	*Visual	NONE	NONE		
-8	Appearance	scalar	*Visual	NORML	NORML		
38µ 71µ	Odor	scalar	*Visual	NORML	NORML		
	Emulsified Water	scalar	*Visual	>0.05	NEG		
	Free Water	scalar	*Visual		NEG		
-	FLUID PROPERT	IES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	31.5	32.0		
	SAMPLE IMAGES	5	method	limit/base	current	history1	history2
Jan2/24	Color				•	no image	no image
	Bottom					no image	no image
	PrtFilter					no image	no image
an 2/24 -	GRAPHS						
Di	Ferrous Alloys						
	10 iron ]			Pa	article Filter (Ma	.gn: 200 x)	
	a. 5 - nickel					Qu	100 000 3000
	0			24			
	Jan 2/24			Jan2/24			
	Non-ferrous Metal	c					
	<sup>10</sup> T	5					
	copper						
	E 5-			1			
	Jan 2/24			Jan 2/24			
				ſ		' d'	
	Viscosity @ 40°C				Acid Number		
7	Abnormal			HOX E	3		1
Jour	3 30 Abnormal			4 Acid Number (mg KOH/g) .0 .0	U+		
ą				du 0.	5		
	25			Acid	0440		24 +
	Jan2/24			Jan2/24	Jan 2/24		Jan2/24
aboratory Sample No. ab Number Inique Number Test Package	: 06062644	Recieveo Diagnoso Diagnost	1 : 17 ed : 23 iician : Do	ary, NC 2751 Jan 2024 Jan 2024 Jg Bogart	3		ORPORATION 4492 HUNT ST PRYOR, OK US 74361 Ict: OTIS HOLT

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Contact/Location: WEBCHECK IN RAEPRY - OTIS HOLT - RAEPRYOK