

# **OIL ANALYSIS REPORT**

Sample Rating Trend







Machine Id **AW100F** Component Hydraulic System Fluid AW HYDRAULIC OIL ISO 100 (--- GAL)

## DIAGNOSIS

#### Recommendation

Little or no information is provided as to the component and lubricant being tested. Recommendations are therefore generic in nature and may not apply to the current application. Please forward information as to equipment type, reservoir capacity, lubricant type and any pertinent information to allow for a more accurate assessment. Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

#### Wear

All component wear rates are normal.

#### Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The water content is negligible. The system and fluid cleanliness is acceptable.


### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		TO20000255		
Sample Date		Client Info		12 Jan 2024		
Machine Age	hrs	Client Info		0		
Oil Age	hrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	<1		
Chromium	ppm	ASTM D5185m	>20	0		
Nickel	ppm	ASTM D5185m	>20	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>20	1		
Lead	ppm	ASTM D5185m	>20	0		
Copper	ppm	ASTM D5185m	>20	15		
Tin	ppm	ASTM D5185m	>20	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	5		
Barium	ppm	ASTM D5185m	5	0		
Molybdenum	ppm	ASTM D5185m	5	<1		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m	25	8		
Calcium	ppm	ASTM D5185m	200	62		
Phosphorus	ppm	ASTM D5185m	300	339		
Zinc	ppm	ASTM D5185m	370	345		
Sulfur	ppm	ASTM D5185m	2500	1198		
CONTAMINANTS						history 0
		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	<1		
Sodium	ppm	ASTM D5185m	00	<1		
Potassium	ppm	ASTM D5185m	>20	<1		
Water	%	ASTM D6304	>0.05	0.006		
ppm Water	ppm	ASTM D6304		66		
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	1672		
Particles >6µm		ASTM D7647	>1300	233		
Particles >14µm		ASTM D7647	>160	13		
Particles >21µm		ASTM D7647	>40	3		
Particles >38µm		ASTM D7647	>10	0		
Particles >71µm		ASTM D7647	>3	0		
Oil Cleanliness		ISO 4406 (c)	>19/17/14	18/15/11		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.57	0.35		



# **OIL ANALYSIS REPORT**







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
- Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.05	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPER	RTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	100	93.2		
Visc @ 100°C	cSt	ASTM D445	11.2	10.6		
Viscosity Index (VI	) Scale	ASTM D2270	97	95		
SAMPLE IMAGE	ES	method	limit/base	current	history1	history2
F221mp Color				•	no image	no image
Bottom					no image	no image
GRAPHS						
Ferrous Alloys				Particle Count		1.220
			491,520			T <sup>26</sup>
E 6 4			122,880	Eminera		-24
			30,720			-22
2			7 680	Abnormal		-20 20
lan 12/24			Jan 12/24 (per 1 ml			0 440
Jan			Jan 12/200			-18 6.19
Non-ferrous Met	als		pitted 480			-16 Cea
15 copper			a 120			-20 (SO 4466:1999 CleanIn ress Code -18 :Code -14 : -14 : -14 : -12 : -1
E 10 - E Transmission lead			30			s Cod
5			30			-12 @
			8	-		-10
			2/24			-8
Jan 1 2/24			Jan12/24		`	
Viscosity @ 40°C				Acid Number	4μ 21μ	38µ 71µ
120 Abaamal			(6)(1,00 9,60 1,00 1,00 1,00 1,00 1,00 1,00 1,00 1			
Direction Abnormal			9.80 P	Base		
G 100 9 100 Base 33 00			ー し.60 - 単 0.40	ф		
90 - Abnormal			U.20	Abnormal		
80			00.0 Acid	42		
Jan 12/24			Jan 12/24	Jan 12/24		Jan 12/2
Laboratory : WearCheck USA - Sample No. : TO2000255 Lab Number : 06062660 Unique Number : 10834042	Recieve Diagnos Diagnos	d :17. ed :18. tician :We		-	HE	DIL COMPANY P.O. BOX 993 NDERSON, TX US 75653
<b>Fest Package</b> : IND 2 (Additional			_			RON NILSSON

Contact: AARON NILSSON awn.nilsson@icloud.com T: (903)807-9576 F:

Certificate L2367