




# OIL ANALYSIS REPORT

Sample Rating Trend

**NORMAL**



Machine Id  
**AC-8 (S/N 18313)**  
 Component  
**Air Compressor**  
 Fluid  
**USPI 5000 AIR 46 (--- QTS)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

## SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	<b>USPM30655</b>	USPM29859	USPM27550
Sample Date	Client Info	<b>10 Jan 2024</b>	03 Oct 2023	29 Jun 2023
Machine Age	hrs Client Info	<b>0</b>	0	0
Oil Age	hrs Client Info	<b>0</b>	0	0
Oil Changed	Client Info	<b>N/A</b>	N/A	N/A
Sample Status		<b>NORMAL</b>	NORMAL	NORMAL

## WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >50	<b>0</b>	0	0
Chromium	ppm ASTM D5185m >4	<b>0</b>	0	0
Nickel	ppm ASTM D5185m >4	<b>0</b>	0	0
Titanium	ppm ASTM D5185m	<b>0</b>	0	<1
Silver	ppm ASTM D5185m	<b>0</b>	0	0
Aluminum	ppm ASTM D5185m >10	<b>&lt;1</b>	0	<1
Lead	ppm ASTM D5185m >20	<b>0</b>	0	0
Copper	ppm ASTM D5185m >40	<b>&lt;1</b>	0	0
Tin	ppm ASTM D5185m >5	<b>0</b>	0	0
Vanadium	ppm ASTM D5185m	<b>0</b>	0	0
Cadmium	ppm ASTM D5185m	<b>0</b>	0	0

## ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m	<b>0</b>	0	0
Barium	ppm ASTM D5185m	<b>0</b>	0	0
Molybdenum	ppm ASTM D5185m	<b>0</b>	0	0
Manganese	ppm ASTM D5185m	<b>&lt;1</b>	0	0
Magnesium	ppm ASTM D5185m	<b>&lt;1</b>	0	0
Calcium	ppm ASTM D5185m	<b>2</b>	<1	2
Phosphorus	ppm ASTM D5185m	<b>28</b>	33	39
Zinc	ppm ASTM D5185m	<b>3</b>	0	0
Sulfur	ppm ASTM D5185m	<b>27</b>	32	41

## CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	<b>0</b>	<1	0
Sodium	ppm ASTM D5185m	<b>0</b>	0	0
Potassium	ppm ASTM D5185m >20	<b>0</b>	<1	0
Water	% ASTM D6304 >0.6	<b>0.006</b>	0.005	0.004
ppm Water	ppm ASTM D6304 >6000	<b>63</b>	59.2	45.6

## FLUID CLEANLINESS






method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647 >10000	<b>245</b>	382	213
Particles >6µm	ASTM D7647 >2500	<b>82</b>	109	83
Particles >14µm	ASTM D7647 >640	<b>14</b>	10	9
Particles >21µm	ASTM D7647 >160	<b>4</b>	2	1
Particles >38µm	ASTM D7647 >40	<b>0</b>	0	0
Particles >71µm	ASTM D7647 >10	<b>0</b>	0	0
Oil Cleanliness	ISO 4406 (c) >20/18/16	<b>15/14/11</b>	16/14/10	15/14/10

## FLUID DEGRADATION

method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g ASTM D8045	<b>0.34</b>	0.33	0.29




# OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.6	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	41.3	46.0	45.8

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



## GRAPHS



**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : USPM30655  
**Lab Number** : 06062776  
**Unique Number** : 10834158  
**Test Package** : IND 2

**KraftHeinz - Granite City - Plant 8354**  
 2901 MISSOURI AVE  
 GRANITE CITY, IL  
 US 62040  
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:  
F: