

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

RECO TYSBLO 2 SWING 2 (S/N M817-260A) Component

Refrigeration Compressor USPI ALT-68 SC (--- GAL)

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil. The amount and size of particulates present in the system are acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





| SAMPLE INFORM | IATION | method | limit/base | current | history1 | history2 |
|------------------|----------|--------------|------------|-------------|-------------|-------------|
| Sample Number | | Client Info | | USP0004826 | USP0001314 | USP05903265 |
| Sample Date | | Client Info | | 09 Jan 2024 | 03 Oct 2023 | 14 Jul 2023 |
| Machine Age | hrs | Client Info | | 136341 | 134952 | 133730 |
| Oil Age | hrs | Client Info | | 0 | 0 | 0 |
| Oil Changed | | Client Info | | N/A | N/A | N/A |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >8 | 0 | 0 | 0 |
| Chromium | ppm | ASTM D5185m | >2 | <1 | 0 | 0 |
| Nickel | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Titanium | ppm | ASTM D5185m | | 0 | <1 | 0 |
| Silver | ppm | ASTM D5185m | >2 | 0 | 0 | <1 |
| Aluminum | ppm | ASTM D5185m | >3 | 0 | 0 | 0 |
| Lead | ppm | ASTM D5185m | >2 | 0 | 0 | 0 |
| Copper | ppm | ASTM D5185m | >8 | 0 | 0 | <1 |
| Tin | ppm | | >4 | 0 | 0 | 0 |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Barium | ppm | ASTM D5185m | | 0 | 1 | 1 |
| Molybdenum | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Manganese | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Magnesium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Calcium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Phosphorus | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Zinc | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Sulfur | ppm | ASTM D5185m | 50 | 0 | 28 | 9 |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >15 | 2 | 2 | 2 |
| Sodium | ppm | ASTM D5185m | | 0 | <1 | 0 |
| Potassium | ppm | ASTM D5185m | >20 | <1 | 0 | <1 |
| Water | % | ASTM D6304 | >0.01 | 0.003 | 0.006 | 0.009 |
| ppm Water | ppm | ASTM D6304 | >100 | 31 | 68.0 | 94.1 |
| FLUID CLEANLIN | IESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | >10000 | 9030 | 5552 | 4648 |
| Particles >6µm | | ASTM D7647 | >2500 | 1285 | 1233 | 1097 |
| Particles >14µm | | ASTM D7647 | >320 | 19 | 30 | 26 |
| Particles >21µm | | ASTM D7647 | >80 | 5 | 4 | 6 |
| Particles >38µm | | ASTM D7647 | >20 | 0 | 0 | 1 |
| Particles >71µm | | ASTM D7647 | >4 | 0 | 0 | 0 |
| Oil Cleanliness | | ISO 4406 (c) | >20/18/15 | 20/17/11 | 20/17/12 | 19/17/12 |
| FLUID DEGRADA | TION | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D974 | 0.005 | 0.015 | 0.016 | 0.013 |



Water (KF)

250

62

60

58

30

Ê 25

[] 201 151

10

5

OIL ANALYSIS REPORT

scalar


scalar


White Metal

Yellow Metal

*Visual

*Visual







an 31/23

Jan31/23


: 17 Jan 2024


: 19 Jan 2024


: Doug Bogart

NONE

NONE







NONE

NONE

NONE

NONE

NONE

NONE

TYSON-BLOUNTSVILE-USP

BLOUNTSVILLE, AL US Contact: SERVICE MANAGER

```
To discuss this sample report, contact Customer Service at 1-800-237-1369.
```

: 06063599

: 10834981

: IND 2

: USP0004826

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Recieved

Diagnosed

Diagnostician

T: F:

Certificate L2367

Laboratory

Sample No.

Lab Number

Unique Number

Test Package