

### **OIL ANALYSIS REPORT**

#### Sample Rating Trend

#### NORMAL

# 30-4 GEA ER1 (S/N Y0609)

Refrigeration Compressor Fluid USPI ALT-68 SC (150 GAL)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear


All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.

#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





| SAMPLE INFORM    | IATION   | method       | limit/base | current     | history1    | history2    |
|------------------|----------|--------------|------------|-------------|-------------|-------------|
| Sample Number    |          | Client Info  |            | USP0004810  | USP0001097  | USP250201   |
| Sample Date      |          | Client Info  |            | 04 Jan 2024 | 11 Oct 2023 | 06 Jul 2023 |
| Machine Age      | hrs      | Client Info  |            | 35800       | 35799       | 35707       |
| Oil Age          | hrs      | Client Info  |            | 0           | 0           | 0           |
| Oil Changed      |          | Client Info  |            | N/A         | N/A         | N/A         |
| Sample Status    |          |              |            | NORMAL      | NORMAL      | NORMAL      |
| WEAR METALS      |          | method       | limit/base | current     | history1    | history2    |
| Iron             | ppm      | ASTM D5185m  | >8         | 0           | 0           | 0           |
| Chromium         | ppm      | ASTM D5185m  | >2         | <1          | 0           | 0           |
| Nickel           | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Titanium         | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Silver           | ppm      | ASTM D5185m  | >2         | 0           | 0           | 0           |
| Aluminum         | ppm      | ASTM D5185m  | >3         | 0           | 0           | <1          |
| Lead             | ppm      | ASTM D5185m  | >2         | 0           | 0           | <1          |
| Copper           | ppm      | ASTM D5185m  | >8         | 0           | 0           | 0           |
| Tin              | ppm      | ASTM D5185m  | >4         | 0           | 0           | 0           |
| Vanadium         | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Cadmium          | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| ADDITIVES        |          | method       | limit/base | current     | history1    | history2    |
| Boron            | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Barium           | ppm      | ASTM D5185m  |            | 3           | 0           | 0           |
| Molybdenum       | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Manganese        | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Magnesium        | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Calcium          | ppm      | ASTM D5185m  |            | <1          | 0           | 0           |
| Phosphorus       | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Zinc             | ppm      | ASTM D5185m  |            | 0           | 0           | 0           |
| Sulfur           | ppm      | ASTM D5185m  | 50         | 0           | 2           | 0           |
| CONTAMINANTS     |          | method       | limit/base | current     | history1    | history2    |
| Silicon          | ppm      | ASTM D5185m  | >15        | 0           | <1          | <1          |
| Sodium           | ppm      | ASTM D5185m  |            | 0           | <1          | 0           |
| Potassium        | ppm      | ASTM D5185m  | >20        | <1          | 0           | 1           |
| Water            | %        | ASTM D6304   | >0.01      | 0.003       | 0.004       | 0.003       |
| ppm Water        | ppm      | ASTM D6304   | >100       | 30          | 42.5        | 30.0        |
| FLUID CLEANLIN   | IESS     | method       | limit/base | current     | history1    | history2    |
| Particles >4µm   |          | ASTM D7647   | >10000     | 5470        | 3402        | 3387        |
| Particles >6µm   |          | ASTM D7647   | >2500      | 1037        | 944         | 904         |
| Particles >14µm  |          | ASTM D7647   | >640       | 22          | 33          | 31          |
| Particles >21µm  |          | ASTM D7647   | >160       | 3           | 4           | 5           |
| Particles >38µm  |          | ASTM D7647   | >40        | 0           | 0           | 0           |
| Particles >71µm  |          | ASTM D7647   | >10        | 0           | 0           | 0           |
| Oil Cleanliness  |          | ISO 4406 (c) | >20/18/16  | 20/17/12    | 19/17/12    | 19/17/12    |
| FLUID DEGRADA    | TION     | method       | limit/base | current     | history1    | history2    |
| Acid Number (AN) | mg KOH/g | ASTM D974    | 0.005      | 0.014       | 0.014       | 0.013       |



Water (KF)

250

200 <u>و</u>150 Water 100

50

n

75

7

cSt (40°C)

60

55

30 Ē 25

20k 15k


n


40 10

0ct7/ lct19/

Ahnorma


## **OIL ANALYSIS REPORT**





|                  |        |           |            |         |          | · · · · · · · · · · · · · · · · · · · |
|------------------|--------|-----------|------------|---------|----------|---------------------------------------|
| White Metal      | scalar | *Visual   | NONE       | NONE    | NONE     | NONE                                  |
| Yellow Metal     | scalar | *Visual   | NONE       | NONE    | NONE     | NONE                                  |
| Precipitate      | scalar | *Visual   | NONE       | NONE    | NONE     | NONE                                  |
| Silt             | scalar | *Visual   | NONE       | NONE    | NONE     | NONE                                  |
| Debris           | scalar | *Visual   | NONE       | NONE    | NONE     | NONE                                  |
| Sand/Dirt        | scalar | *Visual   | NONE       | NONE    | NONE     | NONE                                  |
| Appearance       | scalar | *Visual   | NORML      | NORML   | NORML    | NORML                                 |
| Odor             | scalar | *Visual   | NORML      | NORML   | NORML    | NORML                                 |
| Emulsified Water | scalar | *Visual   | >0.01      | NEG     | NEG      | NEG                                   |
| Free Water       | scalar | *Visual   |            | NEG     | NEG      | NEG                                   |
| FLUID PROPERT    | IES    | method    | limit/base | current | history1 | history2                              |
| Visc @ 40°C      | cSt    | ASTM D445 | 65.6       | 65.7    | 66.2     | 66.2                                  |
| SAMPLE IMAGES    | ;      | method    | limit/base | current | history1 | history2                              |
| Color            |        |           |            |         |          |                                       |
| Bottom           |        |           |            |         |          |                                       |





Contact/Location: ? ? - KRANEWUSP