


OIL ANALYSIS REPORT

Sample Rating Trend







Machine Id 1724 Component

Diesel Engine

DIESEL ENGINE OIL SAE 15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample. Please specify the brand, type, and viscosity of the oil on your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

| | | Mar2022 N | ay2022 Aug2022 Nov20 | 22 Jul2023 Aug2023 Oct2023 | Jan 2024 | |
|------------------|----------|-------------|----------------------|----------------------------|-------------|-------------|
| SAMPLE INFORM | MATION | method | limit/base | current | history1 | history2 |
| Sample Number | | Client Info | | WC0810309 | WC0860427 | WC0844951 |
| Sample Date | | Client Info | | 05 Jan 2024 | 23 Oct 2023 | 18 Aug 2023 |
| Machine Age | mls | Client Info | | 192780 | 187287 | 181843 |
| Oil Age | mls | Client Info | | 0 | 6000 | 0 |
| Oil Changed | | Client Info | | N/A | Changed | Changed |
| Sample Status | | | | NORMAL | NORMAL | NORMAL |
| CONTAMINATION | ١ | method | limit/base | current | history1 | history2 |
| Fuel | | WC Method | >5 | <1.0 | <1.0 | <1.0 |
| Water | | WC Method | >0.2 | NEG | NEG | NEG |
| Glycol | | WC Method | | NEG | NEG | NEG |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >100 | 6 | 4 | 4 |
| Chromium | ppm | ASTM D5185m | >20 | <1 | 0 | <1 |
| Nickel | ppm | ASTM D5185m | >4 | 0 | 0 | 0 |
| Titanium | ppm | ASTM D5185m | | 0 | <1 | <1 |
| Silver | ppm | ASTM D5185m | >3 | 0 | 0 | 0 |
| Aluminum | ppm | ASTM D5185m | >20 | 2 | 4 | 6 |
| Lead | ppm | ASTM D5185m | >40 | 0 | <1 | 0 |
| Copper | ppm | ASTM D5185m | >330 | 18 | 4 | <1 |
| Tin | ppm | ASTM D5185m | >15 | <1 | 0 | <1 |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | 0 |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 250 | 110 | 146 | 29 |
| Barium | ppm | ASTM D5185m | 10 | 3 | 0 | 0 |
| Molybdenum | ppm | ASTM D5185m | 100 | 82 | 71 | 77 |
| Manganese | ppm | ASTM D5185m | | 0 | 0 | <1 |
| Magnesium | ppm | ASTM D5185m | 450 | 232 | 256 | 277 |
| Calcium | ppm | ASTM D5185m | 3000 | 1680 | 1463 | 2135 |
| Phosphorus | ppm | ASTM D5185m | 1150 | 884 | 837 | 1124 |
| Zinc | ppm | ASTM D5185m | 1350 | 1159 | 1166 | 1386 |
| Sulfur | ppm | ASTM D5185m | 4250 | 3419 | 2830 | 4450 |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >25 | 8 | 9 | 8 |
| Sodium | ppm | ASTM D5185m | >158 | 2 | 4 | 5 |
| Potassium | ppm | ASTM D5185m | >20 | 2 | 1 | 0 |
| INFRA-RED | | method | limit/base | current | history1 | history2 |
| Soot % | % | *ASTM D7844 | >3 | 0.3 | 0.3 | 0.3 |
| Nitration | Abs/cm | *ASTM D7624 | >20 | 8.9 | 8.4 | 8.9 |
| Sulfation | Abs/.1mm | *ASTM D7415 | >30 | 21.3 | 20.3 | 19.7 |
| FLUID DEGRADA | TION | method | limit/base | current | history1 | history2 |
| Oxidation | Abs/.1mm | *ASTM D7414 | >25 | 18.4 | 16.9 | 16.0 |
| Base Number (BN) | mg KOH/g | ASTM D2896 | 8.5 | 5.4 | 5.8 | 7.4 |



OIL ANALYSIS REPORT








| VISUAL | | method | limit/base | current | history1 | history2 |
|-------------------------|--------|---------|------------|---------|----------|----------|
| White Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Yellow Metal | scalar | *Visual | NONE | NONE | NONE | NONE |
| Precipitate | scalar | *Visual | NONE | NONE | NONE | NONE |
| Silt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Debris | scalar | *Visual | NONE | NONE | NONE | NONE |
| Sand/Dirt | scalar | *Visual | NONE | NONE | NONE | NONE |
| Appearance | scalar | *Visual | NORML | NORML | NORML | NORML |
| Odor | scalar | *Visual | NORML | NORML | NORML | NORML |
| Emulsified Water | scalar | *Visual | >0.2 | NEG | NEG | NEG |
| Free Water | scalar | *Visual | | NEG | NEG | NEG |


| FLUID PROPERTIES | | method | | | history1 | history2 |
|------------------|-----|-----------|------|------|----------|----------|
| Visc @ 100°C | cSt | ASTM D445 | 14.4 | 13.3 | 13.8 | 14.1 |

GRAPHS













Laboratory Sample No. Lab Number Unique Number : 10835494

: WC0810309 : 06064112 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved : 18 Jan 2024 Diagnosed : 19 Jan 2024

Diagnostician : Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) **TOWN OF CHAPEL HILL** 6900 MILLHOUSE RD

CHAPEL HILL, NC US 27516

Contact: Lisa DePasqua Idepasqua@townofchapelhill.org

T: (919)696-4941