

OIL ANALYSIS REPORT

Sample Rating Trend



ARBURG D-06 - 251627

Hydraulic System Fluid AW HYDRAULIC OIL ISO 46 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

				Jan2024		
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0883592		
Sample Date		Client Info		17 Jan 2024		
Machine Age	yrs	Client Info		0		
Oil Age	yrs	Client Info		0		
Oil Changed		Client Info		N/A		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	4		
Chromium	ppm	ASTM D5185m	>20	0		
Nickel	ppm	ASTM D5185m	>20	0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>20	0		
Lead	ppm	ASTM D5185m	>20	<1		
Copper	ppm	ASTM D5185m	>20	4		
Tin	ppm	ASTM D5185m	>20	<1		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	0		
Barium	ppm	ASTM D5185m	5	0		
Molybdenum	ppm	ASTM D5185m	5	0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m	25	3		
Calcium	ppm	ASTM D5185m	200	70		
Phosphorus	ppm	ASTM D5185m	300	424		
Zinc	ppm	ASTM D5185m	370	528		
Sulfur	ppm	ASTM D5185m	2500	2681		
CONTAMINANTS	}	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m		<1		
Sodium	ppm	ASTM D5185m		3		
Potassium	ppm		>20	۲ ۲		
FLUID CLEANLIN		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	3889		
Particles >6µm		ASTM D7647	>1300	701		
Particles >14µm		ASTM D7647	>160	28		
Particles >21µm		ASTM D7647		6		
Particles >38µm		ASTM D7647	>10	2		
Particles >71µm		ASTM D7647		1		
Oil Cleanliness		ISO 4406 (c)	>19/17/14	19/17/12		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.57	0.68		
36:08) Rev: 1				Contact/Loc	ation JOE SAN	

Report Id: NIAERI [WUSCAR] 06064242 (Generated: 01/20/2024 13:36:08) Rev: 1

Contact/Location: JOE SANDERS - NIAERI




- 1 sa/4


ting 31

2 21

> n. Jan17/24

OIL ANALYSIS REPORT





NONE

NONE

NONE

NONE NONE

NONE

NORML

NORML

NEG

NEG

52.6

NONE

NONE

NONE

NONE

NONE

NONE

NORML

NORML

>0.05

46

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (814)868-3671 x:5131

F: (814)868-9875

Certificate L2367