


## **OIL ANALYSIS REPORT**

### Sample Rating Trend





#### Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

### Wear


All component wear rates are normal.

### Contamination

The system cleanliness is acceptable for your target ISO 4406 cleanliness code. The system and fluid cleanliness is acceptable.

#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.






SAMPLE INFORM	ΛΑΤΙΟΝ	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0843468	WC0803177	WC0763507
Sample Date		Client Info		15 Jan 2024	12 Oct 2023	12 Jul 2023
Machine Age	hrs	Client Info		588	0	457
Oil Age	hrs	Client Info		50	0	100
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m		3	<1	3
Chromium	ppm	ASTM D5185m		ر 1	<1	0
Nickel	ppm	ASTM D5185m		0	<1	0
Titanium	ppm	ASTM D5185m	>10	۰ <1	<1	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>10	2	2	<1
Lead	ppm	ASTM D5185m	>10	1	1	<1
Copper	ppm	ASTM D5185m		6	6	5
Tin	ppm	ASTM D5185m	>10	۰ <1	<1	0
Vanadium	ppm	ASTM D5185m	>10	0	0	<1
Cadmium	ppm	ASTM D5185m		0	<1	0
	ppin			-		-
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		1	9	0
Molybdenum	ppm	ASTM D5185m		11	11	10
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m		5	6	4
Calcium	ppm	ASTM D5185m		164	174	201
Phosphorus	ppm	ASTM D5185m		425	407	417
Zinc	ppm	ASTM D5185m		440	462	466
Sulfur	ppm	ASTM D5185m		1162	1269	1379
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	2	3	2
Sodium	ppm	ASTM D5185m		0	0	1
Potassium	ppm	ASTM D5185m	>20	<1	1	0
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>5000	1053		547
Particles >6µm		ASTM D7647	>1300	212		109
Particles >14µm		ASTM D7647	>160	28		9
Particles >21µm		ASTM D7647		12		2
Particles >38µm		ASTM D7647	>10	2		0
Particles >71µm		ASTM D7647		1		0
Oil Cleanliness		ISO 4406 (c)	>19/17/14	17/15/12		16/14/10
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.38	0.34		0.40
0.50.04) D				0		


Report Id: TLDNOR [WUSCAR] 06065009 (Generated: 01/22/2024 12:50:24) Rev: 1


Contact/Location: Maxime Banctel - TLDNOR




# **OIL ANALYSIS REPORT**










Ē

VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	35.0	34.5	34.6
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				•	no image	
Bottom					no image	



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

Contact/Location: Maxime Banctel - TLDNOR

F: x: