

OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL

FRICK SCMP-2 (S/N 10242A25984230)

Screw Compressor

FRICK COMPRESSOR OIL #9 (150 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


| SAMPLE INFORM | IATION | method | limit/base | current | history1 | history2 |
|------------------|----------|--------------|------------|-------------|----------|----------|
| Sample Number | | Client Info | | WC0893657 | | |
| Sample Date | | Client Info | | 05 Jan 2024 | | |
| Machine Age | hrs | Client Info | | 3155 | | |
| Oil Age | hrs | Client Info | | 3155 | | |
| Oil Changed | | Client Info | | Filtered | | |
| Sample Status | | | | NORMAL | | |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | nnm | ASTM D5185m | >60 | 1 | | |
| Chromium | ppm | ASTM D5185m | >00 | 0 | | |
| Nickel | ppm | ASTM D5185m | 24 | 0 | | |
| | ppm | | | - | | |
| Titanium | ppm | ASTM D5185m | | 0 | | |
| Silver | ppm | ASTM D5185m | - | 0 | | |
| Aluminum | ppm | ASTM D5185m | >5 | 0 | | |
| Lead | ppm | ASTM D5185m | >10 | 0 | | |
| Copper | ppm | ASTM D5185m | >30 | <1 | | |
| Tin | ppm | ASTM D5185m | >15 | 0 | | |
| Vanadium | ppm | ASTM D5185m | | <1 | | |
| Cadmium | ppm | ASTM D5185m | | 0 | | |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | | 0 | | |
| Barium | ppm | ASTM D5185m | | 1 | | |
| Molybdenum | ppm | ASTM D5185m | | 0 | | |
| Manganese | ppm | ASTM D5185m | | 0 | | |
| Magnesium | ppm | ASTM D5185m | | 0 | | |
| Calcium | ppm | ASTM D5185m | | 0 | | |
| Phosphorus | ppm | ASTM D5185m | | 0 | | |
| Zinc | ppm | ASTM D5185m | | 0 | | |
| Sulfur | ppm | ASTM D5185m | | 8 | | |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | ppm | ASTM D5185m | >50 | <1 | | |
| Sodium | ppm | ASTM D5185m | | <1 | | |
| Potassium | ppm | ASTM D5185m | >20 | 0 | | |
| Water | % | ASTM D6304 | >0.1 | 0.003 | | |
| ppm Water | ppm | ASTM D6304 | >1000 | 34 | | |
| FLUID CLEANLIN | ESS | method | limit/base | current | history1 | history2 |
| Particles >4µm | | ASTM D7647 | >10000 | 557 | | |
| Particles >6µm | | ASTM D7647 | >2500 | 118 | | |
| Particles >14µm | | ASTM D7647 | >320 | 7 | | |
| Particles >21µm | | ASTM D7647 | >80 | 2 | | |
| Particles >38µm | | ASTM D7647 | >20 | 0 | | |
| Particles >71µm | | ASTM D7647 | >4 | 0 | | |
| Oil Cleanliness | | ISO 4406 (c) | >20/18/15 | 16/14/10 | | |
| FLUID DEGRADA | TION | method | limit/base | current | history1 | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045 | | 0.014 | | |




OIL ANALYSIS REPORT









To discuss this sample report, contact Customer Service at 1-800-237-1369. rand * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F:

Contact: RANDY UNGER

T: (701)499-1480

randy.unger@northfreezedry.com