


# **OIL ANALYSIS REPORT**

Sample Rating Trend



**NORMAL** 



Machine Id **8174262 (S/N 1792)** 

Component

Compressor

KAESER SIGMA (OEM) M-460 (--- GAL)

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

### Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.


### **Fluid Condition**

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

|                  |          |               | Sep2022    | Jan2024     |             |          |
|------------------|----------|---------------|------------|-------------|-------------|----------|
| SAMPLE INFORM    | MATION   | method        | limit/base | current     | history1    | history2 |
| Sample Number    |          | Client Info   |            | KCPA011740  | KCP46822    |          |
| Sample Date      |          | Client Info   |            | 09 Jan 2024 | 18 Sep 2022 |          |
| Machine Age      | hrs      | Client Info   |            | 1241        | 518         |          |
| Oil Age          | hrs      | Client Info   |            | 0           | 518         |          |
| Oil Changed      | 1110     | Client Info   |            | N/A         | Changed     |          |
| Sample Status    |          | Chorte trillo |            | NORMAL      | NORMAL      |          |
| WEAR METALS      |          | method        | limit/base | current     | history1    | history2 |
| Iron             | ppm      | ASTM D5185m   | >50        | 0           | <1          |          |
| Chromium         | ppm      | ASTM D5185m   | >10        | 0           | 0           |          |
| Nickel           | ppm      | ASTM D5185m   | >3         | 0           | 0           |          |
| Titanium         | ppm      | ASTM D5185m   |            | 0           | 0           |          |
| Silver           | ppm      | ASTM D5185m   | >2         | 0           | 0           |          |
| Aluminum         | ppm      | ASTM D5185m   |            | 0           | <1          |          |
| Lead             | ppm      | ASTM D5185m   | >10        | 0           | 0           |          |
| Copper           | ppm      | ASTM D5185m   |            | <1          | 1           |          |
| Tin              | ppm      | ASTM D5185m   | >10        | 0           | 0           |          |
| Vanadium         | ppm      | ASTM D5185m   | 710        | 0           | 0           |          |
| Cadmium          | ppm      | ASTM D5185m   |            | 0           | 0           |          |
| ADDITIVES        | PPIII    | method        | limit/base | current     | history1    | history2 |
|                  |          |               |            |             | •           | •        |
| Boron            | ppm      | ASTM D5185m   | 0          | 0           | 0           |          |
| Barium           | ppm      | ASTM D5185m   | 90         | 4           | 15          |          |
| Molybdenum       | ppm      | ASTM D5185m   | 0          | 0           | 0           |          |
| Manganese        | ppm      | ASTM D5185m   |            | 0           | <1          |          |
| Magnesium        | ppm      | ASTM D5185m   | 100        | 70          | 77          |          |
| Calcium          | ppm      | ASTM D5185m   | 0          | 0           | 0           |          |
| Phosphorus       | ppm      | ASTM D5185m   | 0          | 0           | 0           |          |
| Zinc             | ppm      | ASTM D5185m   | 0          | 0           | 2           |          |
| Sulfur           | ppm      | ASTM D5185m   | 23500      | 17720       | 21249       |          |
| CONTAMINANTS     |          | method        | limit/base | current     | history1    | history2 |
| Silicon          | ppm      | ASTM D5185m   | >25        | 0           | <1          |          |
| Sodium           | ppm      | ASTM D5185m   |            | 4           | 9           |          |
| Potassium        | ppm      | ASTM D5185m   | >20        | <1          | 2           |          |
| Water            | %        | ASTM D6304    | >0.05      | 0.016       | 0.023       |          |
| ppm Water        | ppm      | ASTM D6304    | >500       | 161         | 236.2       |          |
| FLUID CLEANLIN   | ESS      | method        | limit/base | current     | history1    | history2 |
| Particles >4µm   |          | ASTM D7647    |            | 973         | 521         |          |
| Particles >6µm   |          | ASTM D7647    | >1300      | 218         | 248         |          |
| Particles >14µm  |          | ASTM D7647    | >80        | 17          | 38          |          |
| Particles >21µm  |          | ASTM D7647    | >20        | 4           | 8           |          |
| Particles >38µm  |          | ASTM D7647    | >4         | 1           | 0           |          |
| Particles >71µm  |          | ASTM D7647    | >3         | 0           | 0           |          |
| Oil Cleanliness  |          | ISO 4406 (c)  | >/17/13    | 17/15/11    | 16/15/12    |          |
| FLUID DEGRADA    | TION     | method        | limit/base | current     | history1    | history2 |
| Acid Number (AN) | mg KOH/g | ASTM D8045    | 1.0        | 0.35        | 0.34        |          |



## **OIL ANALYSIS REPORT**



\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:

F: