

### **OIL ANALYSIS REPORT**

# KAESER AS 25T 4899148 (S/N 1337)

Compressor

KAESER SIGMA (OEM) M-460 (--- GAL)

#### DIAGNOSIS

#### Recommendation

Resample at the next service interval to monitor.

#### Wear


All component wear rates are normal.

#### Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

#### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



SAMPLE INFORM		method	limit/base	current	history1	history2
		Client Info		KCPA010961	KCPA002998	KCP46304
Sample Number Sample Date		Client Info		15 Dec 2023	1.017.002000	
Machine Age	hrs	Client Info		46364	19 Aug 2023 44616	09 Sep 2022 36957
Oil Age	hrs	Client Info		40304	0	100
Oil Changed	1115	Client Info		N/A	N/A	Changed
Sample Status		Client Inio		NORMAL	ABNORMAL	ATTENTION
· ·				-	-	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	<1
Chromium	ppm	ASTM D5185m	>10	0	0	0
Nickel	ppm	ASTM D5185m	>3	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	<1
Aluminum	ppm	ASTM D5185m	>10	0	4	<1
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>50	2	12	3
Tin	ppm	ASTM D5185m	>10	0	<1	0
Antimony	ppm	ASTM D5185m				
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	0
Barium	ppm	ASTM D5185m	90	18	0	52
Molybdenum	ppm	ASTM D5185m	0	0	0	0
Manganese	ppm	ASTM D5185m		0	<1	<1
Magnesium	ppm	ASTM D5185m	100	42	<1	66
Calcium	ppm	ASTM D5185m	0	0	0	<1
Phosphorus	ppm	ASTM D5185m	0	0	3	7
Zinc	ppm	ASTM D5185m	0	2	5	5
Sulfur	ppm	ASTM D5185m	23500	17738	21578	16791
CONTAMINANTS	\$	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	<1	0
Sodium	ppm	ASTM D5185m		11	2	2
Potassium	ppm	ASTM D5185m	>20	0	<1	0
Water	%	ASTM D6304	>0.05	0.014	0.008	0.030
ppm Water	ppm	ASTM D6304		145	86.4	306.3
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		3273	7485	11351
Particles >6µm		ASTM D7647	>1300	881	<b>4</b> 117	<b>1</b> 454
Particles >14µm		ASTM D7647	>80	41	<b>6</b> 93	53
Particles >21µm		ASTM D7647	>20	9	<b>1</b> 217	13
Particles >38µm		ASTM D7647	>4	0	<b>1</b> 0	0
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>/17/13	19/17/13	▲ 20/19/17	<b>1</b> 21/18/13
FLUID DEGRADA		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.37	0.42	0.40
	ing itoring	, 10 1 11 00040			taat/Lagation: 2	


Report Id: CARFREMD [WUSCAR] 06073933 (Generated: 02/01/2024 13:49:40) Rev: 1


Contact/Location: ? ? - CARFREMD


Page 1 of 2




## **OIL ANALYSIS REPORT**








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	45	46.5	48.3	45.5
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				a.		



Bottom



\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: ? ? - CARFREMD