

OIL ANALYSIS REPORT

KAESER ASD-40 5570877 (S/N 1249)

Compressor

KAESER SIGMA (OEM) S-460 (--- GAL)

DIAGNOSIS

Recommendation

The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is a moderate amount of particulates present in the oil.

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.





SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KC122303	KC101459	KC107545
Sample Date		Client Info		08 Jan 2024	24 May 2023	13 Oct 2022
Machine Age	hrs	Client Info		38694	35781	31481
Oil Age	hrs	Client Info		0	0	6000
Oil Changed		Client Info		N/A	Not Changd	Changed
Sample Status				ATTENTION	ABNORMAL	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0	0	0
Chromium	ppm	ASTM D5185m	>10	0	<1	0
Nickel	ppm	ASTM D5185m	>3	0	0	0
Titanium	ppm	ASTM D5185m	>3	0	0	0
Silver	ppm	ASTM D5185m	>2	0	<1	<1
Aluminum	ppm	ASTM D5185m	>10	0	<1	<1
Lead	ppm	ASTM D5185m	>10	0	<1	0
Copper	ppm	ASTM D5185m	>50	9	6	10
Tin	ppm	ASTM D5185m	>10	0	0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m	90	0	0	0
Molybdenum	ppm	ASTM D5185m		0	<1	0
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m	90	0	35	0
Calcium	ppm	ASTM D5185m	2	0	0	0
Phosphorus	ppm	ASTM D5185m		0	0	2
Zinc	ppm	ASTM D5185m		3	14	0
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	0	<1	0
Sodium	ppm	ASTM D5185m		4	9	0
Potassium	ppm	ASTM D5185m	>20	0	3	1
Water	%	ASTM D6304	>0.05	0.007	0.009	0.003
ppm Water	ppm	ASTM D6304	>500	76	90.7	34.7
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		3912		20544
Particles >6µm		ASTM D7647	>1300	1 584		<u> </u>
Particles >14µm		ASTM D7647	>80	1 47		<u> </u>
		ASTM D7647	>20	A 33		<u> </u>
Particles >21µm				— 33		
Particles >38µm		ASTM D7647	>4	1		▲ 59
Particles >38µm Particles >71µm		ASTM D7647 ASTM D7647	>4 >3	1 1		▲ 59▲ 3
Particles >38µm		ASTM D7647	>4	1		▲ 59
Particles >38µm Particles >71µm		ASTM D7647 ASTM D7647	>4 >3	1 1		▲ 59▲ 3



OIL ANALYSIS REPORT








VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	🔺 MODER	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	ΓIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	44.6	44.7	44.6
SAMPLE IMAGE	S	method	limit/base	current	history1	history2
Color				•		
Bottom						

ttom



Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: ? ? - WILJEF

Page 2 of 2

F: