

# **OIL ANALYSIS REPORT**

## Sample Rating Trend

# DIRT

# TRANE FBI ACADEMY ERF 2 (S/N L07H04124)

**Refrigeration Compressor** 

**TRANE 0022 (9 GAL)** 

## **DIAGNOSIS**

## Recommendation

No corrective action is recommended at this time. We recommend an early resample to monitor this condition.

All component wear rates are normal.

## Contamination

Elemental level of silicon (Si) above normal.


## **Fluid Condition**


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


		Jan 2015 C	lec2015 Feb2017 Jan201	8 Sep2018 Jan2021 Jan2022	Jan2024	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0814425	WC0525391	WC0384440
Sample Date		Client Info		15 Jan 2024	18 Jan 2022	07 Jan 2021
Machine Age	hrs	Client Info		23642	20801	19461
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				ABNORMAL	ABNORMAL	ABNORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>8	1	1	<1
Chromium	ppm	ASTM D5185m	>2	<1	0	0
Nickel	ppm	ASTM D5185m		0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m	>2	0	<1	0
Aluminum	ppm	ASTM D5185m	>3	2	0	<1
Lead	ppm	ASTM D5185m	>2	<1	0	4
Copper	ppm	ASTM D5185m	>8	1	<1	<1
Tin	ppm	ASTM D5185m	>4	3	2	<1
Antimony	ppm	ASTM D5185m			0	2
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	<1
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	<1	<1
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		<1	0	0
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m		0	<1	<1
Calcium	ppm	ASTM D5185m		0	0	0
Phosphorus	ppm	ASTM D5185m		0	<1	4
Zinc	ppm	ASTM D5185m		0	0	0
Sulfur	ppm	ASTM D5185m		0	0	0
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	<u>^</u> 25	<u>^</u> 27	<u>^</u> 21
Sodium	ppm	ASTM D5185m		0	<1	<1
Potassium	ppm	ASTM D5185m	>20	2	<1	0
Water	%	ASTM D6304	>0.005	0.004	0.001	0.002
ppm Water	ppm	ASTM D6304	>50	49	1.1	15.7
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974		0.056	0.012	0.016




## **OIL ANALYSIS REPORT**










VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
<b>Emulsified Water</b>	scalar	*Visual	>0.005	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERTIES		method	limit/base	current	history1	history2

Visc @ 40°C	cSt	ASTM D445		45.6	44.5	44.3
SAMPLE IMAGE	ES	method	limit/base	current	history1	history2


Color







## **GRAPHS**

Ferrous Alloys Non-ferrous Metals











Certificate L2367

Laboratory Sample No.

Test Package : IND 2

: WC0814425 Lab Number : 06074121 Unique Number: 10856212

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received **Tested** 

Diagnosed

: 30 Jan 2024 : 31 Jan 2024 : 31 Jan 2024 - Jonathan Hester

**DAIKIN APPLIED** 5021 HOWERTON WAY SUITE P

BOWIE, MD US 20715

Contact: ANDREW TURLINGTON andrew.turlington@daikinapplied.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (301)735-1838

T: (301)735-1440