KAESER COMPRESSORS
Built for a lifetime.

OIL ANALYSIS REPORT

Sample Rating Trend



VIS DEBRIS

Machine Id
6893557 (S/N 1532)
Component
Compressor
Fluid
KAESER SIGMA (OEM) FG-460 (--- GAL)

DIAGNOSIS

Recommendation
No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor. We were unable to perform a particle count due to a high concentration of particles present in this sample.

Wear
All component wear rates are normal.

Contamination
High concentration of visible dirt/debris present in the oil.

Fluid Condition
The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number		Client Info		**KC120922**	KC108004	KC101623
Sample Date		Client Info		**22 Jan 2024**	25 Oct 2023	25 Jul 2023
Machine Age	hrs	Client Info		**18542**	16963	15709
Oil Age	hrs	Client Info		**0**	1254	2377
Oil Changed		Client Info		**N/A**	Not Changd	Changed
Sample Status				**ABNORMAL**	ABNORMAL	ABNORMAL

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	**0**	1	<1
Chromium	ppm	ASTM D5185m	>10	**<1**	<1	0
Nickel	ppm	ASTM D5185m	>3	**<1**	0	0
Titanium	ppm	ASTM D5185m	>3	**<1**	0	0
Silver	ppm	ASTM D5185m	>2	**0**	0	0
Aluminum	ppm	ASTM D5185m	>10	**4**	2	4
Lead	ppm	ASTM D5185m	>10	**<1**	0	0
Copper	ppm	ASTM D5185m	>50	**7**	7	3
Tin	ppm	ASTM D5185m	>10	**<1**	<1	<1
Vanadium	ppm	ASTM D5185m		**0**	0	0
Cadmium	ppm	ASTM D5185m		**0**	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		**0**	0	0
Barium	ppm	ASTM D5185m		**0**	20	2
Molybdenum	ppm	ASTM D5185m		**<1**	0	0
Manganese	ppm	ASTM D5185m		**0**	<1	0
Magnesium	ppm	ASTM D5185m		**2**	2	<1
Calcium	ppm	ASTM D5185m		**0**	<1	0
Phosphorus	ppm	ASTM D5185m	500	**104**	212	84
Zinc	ppm	ASTM D5185m		**68**	135	83

CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	**0**	0	0
Sodium	ppm	ASTM D5185m		**0**	5	0
Potassium	ppm	ASTM D5185m	>20	**2**	0	<1
Water	%	ASTM D6304	>0.05	**0.018**	0.002	0.002
ppm Water	ppm	ASTM D6304	>500	**189**	18.1	22.2

FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		**---**	74869	11167
Particles >6µm		ASTM D7647	>1300	**---**	▲ 33251	▲ 3342
Particles >14µm		ASTM D7647	>80	**---**	▲ 2921	▲ 190
Particles >21µm		ASTM D7647	>20	**---**	▲ 728	▲ 43
Particles >38µm		ASTM D7647	>4	**---**	▲ 27	2
Particles >71µm		ASTM D7647	>3	**---**	▲ 3	0
Oil Cleanliness		ISO 4406 (c)	>--/17/13	**---**	▲ 23/22/19	▲ 21/19/15

FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	1.5	**0.41**	0.49	0.30

KAESER COMPRESSORS
Built for a lifetime.

OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	**NONE**	NONE	NONE
Precipitate	scalar	*Visual	NONE	**NONE**	NONE	NONE
Silt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Debris	scalar	*Visual	NONE	▲ **HEAVY**	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	**NONE**	NONE	NONE
Appearance	scalar	*Visual	NORML	**NORML**	NORML	NORML
Odor	scalar	*Visual	NORML	**NORML**	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	**NEG**	NEG	NEG
Free Water	scalar	*Visual		**NEG**	NEG	NEG

FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	**48.9**	47.2	47.8

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					
Bottom					

GRAPHS









Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : KC120922
Lab Number : 06074769
Unique Number : 10856860
Test Package : IND 2

Recieved : 30 Jan 2024
Diagnosed : 31 Jan 2024
Diagnostician : Doug Bogart

NICHOLAS MEATS
508 E VALLEY RD
LOGANTON, PA
US 17747
Contact: Service Manager
T:
F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.
** - Denotes test methods that are outside of the ISO 17025 scope of accreditation.*
Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)