

OIL ANALYSIS REPORT

Sample Rating Trend



GREENERD 1531 Component **Hydraulic System**

MOBIL DTE 25 (250 GAL)

A Recommendation

Resample at the next service interval to monitor. Due to an abnormal test result it is recommended to contact Stauff Corp at (201)-444-7800 for help resolving the issue.

Wear

All component wear rates are normal.

Contamination

There is a moderate amount of silt (particulates < 6 microns in size) present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


		Nov2016	Nov2017 Nov2018	Jan2021 Jan2022	Jan2024	
SAMPLE INFORM	ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		ST44447	ST42709	ST40908
Sample Date		Client Info		19 Jan 2024	20 Jan 2022	12 Jan 2021
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				ATTENTION	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	3	4	4
Chromium	ppm	ASTM D5185m	>20	0	0	0
Nickel	ppm	ASTM D5185m	>20	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	0	<1	0
Lead	ppm	ASTM D5185m	>20	<1	<1	<1
Copper	ppm	ASTM D5185m		13	14	14
Tin	ppm	ASTM D5185m	>20	<1	<1	0
Antimony	ppm	ASTM D5185m			0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		2	2	2
ADDITIVES	le le co	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	innibacco	0	2	4
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum		ASTM D5185m		۰ <1	<1	<1
Manganese	ppm	ASTM D5185m		0	<1	0
Magnesium	ppm	ASTM D5185m		10	12	11
Calcium	ppm	ASTM D5185m		137	145	145
	ppm	ASTM D5185m		571	530	530
Phosphorus Zinc	ppm ppm	ASTM D5185m		790	752	730
Sulfur		ASTM D5185m		6944	5638	5885
	ppm					
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	1	1	<1
Sodium	ppm	ASTM D5185m		4	4	4
Potassium	ppm	ASTM D5185m	>20	2	<1	<1
Water	%	ASTM D6304	>0.05	0.014	0.014	0.018
ppm Water	ppm	ASTM D6304	>500	142	142.6	183.4
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>2500	2614	2014	1203
Particles >6µm		ASTM D7647	>640	488	202	139
Particles >14µm		ASTM D7647	>80	25	14	11
Particles >21µm		ASTM D7647	>20	5	6	3
Particles >38µm		ASTM D7647	>4	0	0	0
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>18/16/13	1 9/16/12	18/15/11	17/14/11
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.95	0.93	0.867


Report Id: LARATT [WUSCAR] 06074785 (Generated: 02/02/2024 15:18:31) Rev: 1


Contact/Location: GARY BRUNE - LARATT



OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	IES	method			history1	history2
FLUID PROPERT Visc @ 40°C	CIES cSt	method ASTM D445	limit/base 44.2	current 43.1	history1 46.4	history2 45.8
	cSt					
Visc @ 40°C	cSt	ASTM D445	44.2 limit/base	43.1	46.4	45.8

