

OIL ANALYSIS REPORT

Sample Rating Trend


ISO

Bulk Oil Storage Petro Canada Turboflo XL 32

Component

Reservoir Turbine

PETRO CANADA TURBOFLO XL32 (55 GAL)





DIAGNOSIS

Recommendation

We recommend you service the filters on this component if applicable. Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is a high amount of particulates present in the oil.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

L)		ep2018 Se	p2019 Jul2020 Ju	12021 Apr2022 Jan2023	Oct2023	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0886164	WC0816902	WC0635837
Sample Date		Client Info		24 Jan 2024	30 Oct 2023	26 Jul 2023
Machine Age	mths	Client Info		0	0	0
Oil Age	mths	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				ABNORMAL	NORMAL	NORMAL
CONTAMINATION	١	method	limit/base	current	history1	history2
Water		WC Method	>0.03	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>15	0	0	0
Chromium	ppm	ASTM D5185m	>4	0	0	0
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>10	0	0	0
Lead	ppm	ASTM D5185m		0	0	0
Copper	ppm	ASTM D5185m	>5	0	<1	0
Tin	ppm	ASTM D5185m	>5	<1	0	0
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	0
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	0	0	0
Manganese	ppm	ASTM D5185m	0	<1	0	0
Magnesium	ppm	ASTM D5185m	0	0	0	2
Calcium	ppm	ASTM D5185m	0	0	<1	0
Phosphorus	ppm	ASTM D5185m	5	<1	<1	0
Zinc	ppm	ASTM D5185m	0	0	0	0
Sulfur	ppm	ASTM D5185m	750	738	712	920
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	<1	0	0
Sodium	ppm	ASTM D5185m		<1	<1	0
Potassium	ppm	ASTM D5185m	>20	0	<1	0
FLUID CLEANLIN	ESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>2500	<u> </u>	1208	1088
Particles >6µm		ASTM D7647	>640	<u> </u>	308	403
Particles >14μm		ASTM D7647	>80	<u>239</u>	23	57
Particles >21µm		ASTM D7647	>20	<u>^</u> 50	4	14
Particles >38μm		ASTM D7647	>4	2	0	1
Particles >71µm		ASTM D7647	>3	0	0	0
Oil Cleanliness		ISO 4406 (c)	>18/16/13	<u> </u>	17/15/12	17/16/13
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.04	0.055	0.168	0.052



OIL ANALYSIS REPORT



method	limit/base	current	history1	history2
ar *Visual	NONE	NONE	NONE	NONE
ar *Visual	NONE	NONE	NONE	NONE
ar *Visual	NONE	NONE	NONE	NONE
ar *Visual	NONE	NONE	NONE	NONE
ar *Visual	NONE	NONE	NONE	NONE
ar *Visual	NONE	NONE	NONE	NONE
ar *Visual	NORML	NORML	NORML	NORML
ar *Visual	NORML	NORML	NORML	NORML
ar *Visual	>0.03	NEG	NEG	NEG
ar *Visual		NEG	NEG	NEG
method	limit/hasa	current	history1	history2
	ar *Visual	ar *Visual NONE lar *Visual NORML	ar *Visual NONE NONE lar *Visual NORML NORML	ar *Visual NONE NONE NONE lar *Visual NORML NORML NORML NORML lar *Visual NORML NORML NORML NORML lar *Visual NORML NORML NORML NORML NORML lar *Visual NORML NORML NORML NORML NORML NORML NORML lar *Visual NORML NORM


_ =	4µm			
E 15k	14µm			
83				
O I				
Dartic 10k				
10k - 10k				
10k - John Tuber of participants				
15k - 15k - 16k -	omal			
popular of particular of parti	omial			
object 10k	omal	Garage prompt		


cSt Visc @ 40°C ASTM D445 33.86 34.2 33.9 34.0 SAMPLE IMAGES method limit/base current history1

Color

Bottom







GRAPHS Ferrous Alloys A Particle Count 491 520 122,880 30.72 Jul21/20 Non-ferrous Metals 480 120 Viscosity @ 40°C Acid Number 08.0 08.0 09.0 09.0





Certificate L2367

Laboratory Sample No. Lab Number **Unique Number** Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0886164 : 06075727

: 10857818

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: 31 Jan 2024 Recieved Diagnosed Diagnostician : Don Baldridge

: 01 Feb 2024

INGREDION INC

WINSTON SALEM PLANT, 4501 OVERDALE ROAD WINSTON SALEM, NC

US 27107

Contact: MATTHEW KING matthew.king@ingredion.com

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: F: (336)785-8809