

# **OIL ANALYSIS REPORT**

Area **25** [25] A25 FAN 1

**Center Gearbox** 

**GEAR LIFE 220 (5 GAL)** 

# -----

Sample Rating Trend



# Recommendation

Resample at the next service interval to monitor. ( Customer Sample Comment: Gear Life 220 )

All component wear rates are normal.

# Contamination

There is no indication of any contamination in the oil.


# **Fluid Condition**


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		HPL0002399	HPL0003584	HPL0003185
Sample Date		Client Info		30 Jan 2024	30 Oct 2023	18 Jul 2023
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		1620	0	0
Oil Changed		Client Info		Not Changd	Changed	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	V	method	limit/base	current	history1	history2
Water		WC Method	>0.2	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	66	38	86
Chromium	ppm	ASTM D5185m	>10	<1	0	1
Nickel	ppm	ASTM D5185m	>10	0	0	<1
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>25	<1	0	1
Lead	ppm	ASTM D5185m	>50	0	0	0
Copper	ppm	ASTM D5185m	>200	0	0	<1
Tin	ppm	ASTM D5185m	>10	<1	0	<1
Vanadium	ppm	ASTM D5185m		<1	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	<1
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		1	<1	4
Magnesium	ppm	ASTM D5185m		0	0	2
Calcium	ppm	ASTM D5185m		25	21	18
Phosphorus	ppm	ASTM D5185m		108	103	120
Zinc	ppm	ASTM D5185m		0	4	11
Sulfur	ppm	ASTM D5185m		15756	17118	22427
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>50	2	3	9
Sodium	ppm	ASTM D5185m		0	0	<1
Potassium	ppm	ASTM D5185m	>20	<1	<1	<1
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.23	0.21	0.18



# **OIL ANALYSIS REPORT**







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	LIGHT	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPE	NIIEO	method		riistory i	riistoryz
Visc @ 40°C	cSt	ASTM D445	220	218	211


Color	no image	no image	no image
Bottom	no image	no image	no image





SAMPLE IMAGES





















Certificate L2367

Laboratory Sample No.

Lab Number **Unique Number** Test Package : MOB 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : HPL0002399 : 06076397 : 10858488

Recieved Diagnosed

: 31 Jan 2024 : 02 Feb 2024 Diagnostician : Don Baldridge

**KENSING** 2525 S KENSINGTON RD KANKAKEE, IL US 60901

Contact: TIM HUBERT

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. timothy.hubert@kensingsolutions.com T: (815)939-8918

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: x: