




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
OKLAHOMA/105
Machine Id
08.505 [OKLAHOMA^105]
Component
Diesel Engine
Fluid
MOBIL DELVAC 1300 SUPER15W40 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0886950	WC0807919	WC0746347
Sample Date	Client Info		29 Jan 2024	25 May 2023	11 Nov 2022
Machine Age	hrs	Client Info	4645	3485	2610
Oil Age	hrs	Client Info	1160	875	980
Oil Changed	Client Info		Changed	Changed	Changed
Sample Status			NORMAL	NORMAL	SEVERE

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>3.0	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >90	58	17	▲ 156
Chromium	ppm	ASTM D5185m >20	4	2	▲ 24
Nickel	ppm	ASTM D5185m >2	0	0	0
Titanium	ppm	ASTM D5185m >2	<1	<1	2
Silver	ppm	ASTM D5185m >2	0	<1	0
Aluminum	ppm	ASTM D5185m >20	4	3	▲ 28
Lead	ppm	ASTM D5185m >40	0	1	0
Copper	ppm	ASTM D5185m >330	1	0	3
Tin	ppm	ASTM D5185m >15	<1	<1	<1
Vanadium	ppm	ASTM D5185m	0	0	<1
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	23	39	34
Barium	ppm	ASTM D5185m 0	<1	0	0
Molybdenum	ppm	ASTM D5185m 0	44	45	42
Manganese	ppm	ASTM D5185m	1	1	3
Magnesium	ppm	ASTM D5185m 0	540	563	509
Calcium	ppm	ASTM D5185m	1756	1726	1979
Phosphorus	ppm	ASTM D5185m	774	815	782
Zinc	ppm	ASTM D5185m	960	1006	912
Sulfur	ppm	ASTM D5185m	2289	3037	2951

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	17	8	■ 101
Sodium	ppm	ASTM D5185m	2	3	6
Potassium	ppm	ASTM D5185m >20	<1	2	4

INFRA-RED



	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >6	0.7	0.3	0.4
Nitration	Abs/cm	*ASTM D7624 >20	14.7	8.6	10.3
Sulfation	Abs/.1mm	*ASTM D7415 >30	26.8	23.2	24.6

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	30.6	22.0	23.5
Base Number (BN)	mg KOH/g	ASTM D2896 9.4	5.9	9.8	10.3







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445 14	14.3	13.2	12.8

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0886950 **Received** : 01 Feb 2024
Lab Number : 06076659 **Tested** : 01 Feb 2024
Unique Number : 10858750 **Diagnosed** : 02 Feb 2024 - Don Baldrige
Test Package : CONST (Additional Tests: TBN)

SHERWOOD CONSTRUCTION CO INC
 3219 WEST MAY ST
 WICHITA, KS
 US 67213
 Contact: SHAWN SOUTH
 shawn.south@sherwood.net

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: x:
F: x: