




OIL ANALYSIS REPORT



Area
OKLAHOMA/102/EG - DOZER
 Machine Id
35.101L [OKLAHOMA^102^EG - DOZER]
 Component
Diesel Engine
 Fluid
MOBIL DELVAC 1300 SUPER15W40 (--- GAL)

Sample Rating Trend



WEAR



DIAGNOSIS

Recommendation

Oil and filter change at the time of sampling has been noted. No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

An increase in the iron level is noted. All other component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		WC0873895	WC0857351	WC0819874
Sample Date	Client Info		11 Jan 2024	17 Oct 2023	17 Jul 2023
Machine Age	hrs	Client Info	12101	8898	8667
Oil Age	hrs	Client Info	250	6708	6477
Oil Changed	Client Info		Changed	Changed	N/A
Sample Status			ATTENTION	NORMAL	NORMAL

CONTAMINATION

	method	limit/base	current	history1	history2
Fuel	WC Method	>5	<1.0	<1.0	<1.0
Water	WC Method	>0.2	NEG	NEG	NEG
Glycol	WC Method		NEG	NEG	NEG

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >100	▲ 85	12	16
Chromium	ppm	ASTM D5185m >20	3	<1	<1
Nickel	ppm	ASTM D5185m >2	1	<1	0
Titanium	ppm	ASTM D5185m >2	<1	0	0
Silver	ppm	ASTM D5185m >2	0	0	0
Aluminum	ppm	ASTM D5185m >25	7	3	6
Lead	ppm	ASTM D5185m >40	16	<1	0
Copper	ppm	ASTM D5185m >330	30	<1	<1
Tin	ppm	ASTM D5185m >15	2	<1	<1
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	48	40	38
Barium	ppm	ASTM D5185m 0	<1	0	0
Molybdenum	ppm	ASTM D5185m 0	49	45	44
Manganese	ppm	ASTM D5185m	<1	0	<1
Magnesium	ppm	ASTM D5185m 0	535	511	566
Calcium	ppm	ASTM D5185m	1788	1644	1782
Phosphorus	ppm	ASTM D5185m	795	771	757
Zinc	ppm	ASTM D5185m	944	920	977
Sulfur	ppm	ASTM D5185m	2279	2870	2940

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	18	5	5
Sodium	ppm	ASTM D5185m	6	4	8
Potassium	ppm	ASTM D5185m >20	4	2	1

INFRA-RED

	method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844 >3	1.3	0.2	0.4
Nitration	Abs/cm	*ASTM D7624 >20	12.9	6.7	8.1
Sulfation	Abs/.1mm	*ASTM D7415 >30	28.9	21.0	22.4


FLUID DEGRADATION

	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414 >25	30.9	19.1	20.3
Base Number (BN)	mg KOH/g	ASTM D2896 9.4	7.8	8.9	9.2




OIL ANALYSIS REPORT


▲ Ferrous Alloys



Base Number



Viscosity @ 100°C




VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445 14	14.1	13.3	13.4

GRAPHS


▲ Ferrous Alloys




Non-ferrous Metals



Viscosity @ 100°C



Base Number



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : WC0873895 **Received** : 01 Feb 2024
Lab Number : 06076675 **Tested** : 02 Feb 2024
Unique Number : 10858766 **Diagnosed** : 02 Feb 2024 - Don Baldrige
Test Package : CONST (Additional Tests: TBN)

SHERWOOD CONSTRUCTION CO INC
 3219 WEST MAY ST
 WICHITA, KS
 US 67213
 Contact: DOUG KING
 doug.king@sherwood.net
 T: (316)617-3161
 F: x:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)