


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



109564 Component

Diesel Engine

SHELL ROTELLA T 15W40 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

		Oct2020	Jun 2021 Feb 2022	Oct2022 Jun2023	Jan 2024	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		IL0033064	IL0027512	IL0027731
Sample Date		Client Info		24 Jan 2024	09 Jun 2023	27 Oct 2022
Machine Age	mls	Client Info		136460	117136	93024
Oil Age	mls	Client Info		19324	24112	18962
Oil Changed		Client Info		Changed	Changed	Changed
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	١	method	limit/base	current	history1	history2
Fuel		WC Method	>5	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	35	35	35
Chromium	ppm	ASTM D5185m	>20	1	2	1
Nickel	ppm	ASTM D5185m	>4	<1	<1	0
Titanium	ppm	ASTM D5185m		<1	<1	0
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	13	13	17
Lead	ppm	ASTM D5185m	>40	0	1	0
Copper	ppm	ASTM D5185m	>330	2	1	1
Tin	ppm	ASTM D5185m	>15	<1	<1	0
Antimony	ppm	ASTM D5185m				
Vanadium	ppm	ASTM D5185m		0	<1	0
Cadmium	ppm	ASTM D5185m		0	<1	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	316	45	▲ 28	45
Barium	ppm	ASTM D5185m	0.0	<1	0	0
Molybdenum	ppm	ASTM D5185m	1.2	36	92	44
Manganese	ppm	ASTM D5185m		<1	<1	1
Magnesium	ppm	ASTM D5185m	24	236	A 86	450
Calcium	ppm	ASTM D5185m	2292	1873	2367	1849
Phosphorus	ppm	ASTM D5185m	1064	942	1021	1043
Zinc	ppm	ASTM D5185m	1160	1157	1323	1406
Sulfur	ppm	ASTM D5185m		3164	4409	3526
CONTAMINANTS		method	limit/base	current	history1	history2
					_	
Silicon	ppm	ASTM D5185m	>25	11	7	8
Sodium	ppm	ASTM D5185m		0	3	2
Sodium Potassium						
Sodium Potassium INFRA-RED	ppm ppm	ASTM D5185m ASTM D5185m method	>20 limit/base	0 14 current	3 10 history1	2 19 history2
Sodium Potassium INFRA-RED Soot %	ppm ppm	ASTM D5185m ASTM D5185m method *ASTM D7844	>20 limit/base >3	0 14 current 0.7	3 10 history1 0.6	2 19 history2 0.7
Sodium Potassium INFRA-RED Soot % Nitration	ppm ppm % Abs/cm	ASTM D5185m ASTM D5185m method *ASTM D7844 *ASTM D7624	>20 limit/base >3 >20	0 14 current 0.7 11.9	3 10 history1 0.6 12.6	2 19 history2 0.7 13.6
Sodium Potassium INFRA-RED Soot %	ppm ppm	ASTM D5185m ASTM D5185m method *ASTM D7844	>20 limit/base >3 >20	0 14 current 0.7	3 10 history1 0.6	2 19 history2 0.7
Sodium Potassium INFRA-RED Soot % Nitration	ppm ppm % Abs/cm Abs/.1mm	ASTM D5185m ASTM D5185m method *ASTM D7844 *ASTM D7624 *ASTM D7415 method	>20 limit/base >3 >20	0 14 current 0.7 11.9	3 10 history1 0.6 12.6	2 19 history2 0.7 13.6
Sodium Potassium INFRA-RED Soot % Nitration Sulfation	ppm ppm % Abs/cm Abs/.1mm	ASTM D5185m ASTM D5185m method *ASTM D7844 *ASTM D7624 *ASTM D7415	>20 limit/base >3 >20 >30	0 14 current 0.7 11.9 25.2	3 10 history1 0.6 12.6 26.1	2 19 history2 0.7 13.6 27.8
Sodium Potassium INFRA-RED Soot % Nitration Sulfation FLUID DEGRADA	ppm ppm % Abs/cm Abs/.1mm	ASTM D5185m ASTM D5185m method *ASTM D7844 *ASTM D7624 *ASTM D7415 method	>20 limit/base >3 >20 >3 >20 limit/base	0 14 current 0.7 11.9 25.2 current	3 10 history1 0.6 12.6 26.1 history1	2 19 history2 0.7 13.6 27.8 history2



OIL ANALYSIS REPORT







VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG


FLUID PROPER	IIIES	method	ilmit/base	current	nistory i	nistory2
Visc @ 100°C	cSt	ASTM D445	15.7	13.6	13.4	13.9


GRAPHS

Ferrous Alloys













Certificate L2367

Laboratory Sample No. Lab Number

Unique Number Test Package : FLEET

: IL0033064 : 06076703 : 10858794

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Recieved Diagnosed

: 01 Feb 2024 : 02 Feb 2024 Diagnostician : Wes Davis

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

IDEALEASE OF NORTHWEST WI

611 HANSEN ROAD GREEN BAY, WI US 54304

Contact: GARY KOLTZ gkoltz@pcitrucks.com

> T: (920)499-6200 F: (920)499-5332

Contact/Location: GARY KOLTZ - IDEGREWI