



OIL ANALYSIS REPORT

Sample Rating Trend



ISO



Machine Id
5165306 (S/N 1122)

Component
Compressor

Fluid
KAESER SIGMA (OEM) M-460 (--- GAL)

DIAGNOSIS

▲ Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

▲ Contamination

There is a moderate amount of particulates present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

| method | limit/base | current | history1 | history2 |
|---------------|-----------------|--------------------|----------|----------|
| Sample Number | Client Info | KCPA009295 | --- | --- |
| Sample Date | Client Info | 13 Dec 2023 | --- | --- |
| Machine Age | hrs Client Info | 42877 | --- | --- |
| Oil Age | hrs Client Info | 0 | --- | --- |
| Oil Changed | Client Info | N/A | --- | --- |
| Sample Status | | ATTENTION | --- | --- |

WEAR METALS

| method | limit/base | current | history1 | history2 |
|--------------------------|------------|--------------|----------|----------|
| Iron ppm ASTM D5185m | >50 | 0 | --- | --- |
| Chromium ppm ASTM D5185m | >10 | 0 | --- | --- |
| Nickel ppm ASTM D5185m | >3 | 0 | --- | --- |
| Titanium ppm ASTM D5185m | >3 | <1 | --- | --- |
| Silver ppm ASTM D5185m | >2 | 0 | --- | --- |
| Aluminum ppm ASTM D5185m | >10 | 0 | --- | --- |
| Lead ppm ASTM D5185m | >10 | <1 | --- | --- |
| Copper ppm ASTM D5185m | >50 | 8 | --- | --- |
| Tin ppm ASTM D5185m | >10 | <1 | --- | --- |
| Vanadium ppm ASTM D5185m | | 0 | --- | --- |
| Cadmium ppm ASTM D5185m | | 0 | --- | --- |

ADDITIVES

| method | limit/base | current | history1 | history2 |
|----------------------------|------------|--------------|----------|----------|
| Boron ppm ASTM D5185m | 0 | 0 | --- | --- |
| Barium ppm ASTM D5185m | 90 | 0 | --- | --- |
| Molybdenum ppm ASTM D5185m | 0 | 0 | --- | --- |
| Manganese ppm ASTM D5185m | | 0 | --- | --- |
| Magnesium ppm ASTM D5185m | 100 | 0 | --- | --- |
| Calcium ppm ASTM D5185m | 0 | 0 | --- | --- |
| Phosphorus ppm ASTM D5185m | 0 | 0 | --- | --- |
| Zinc ppm ASTM D5185m | 0 | 0 | --- | --- |
| Sulfur ppm ASTM D5185m | 23500 | 16645 | --- | --- |

CONTAMINANTS

| method | limit/base | current | history1 | history2 |
|---------------------------|------------|--------------|----------|----------|
| Silicon ppm ASTM D5185m | >25 | 0 | --- | --- |
| Sodium ppm ASTM D5185m | | <1 | --- | --- |
| Potassium ppm ASTM D5185m | >20 | 0 | --- | --- |
| Water % ASTM D6304 | >0.05 | 0.010 | --- | --- |
| ppm Water ppm ASTM D6304 | >500 | 100 | --- | --- |





FLUID CLEANLINESS

| method | limit/base | current | history1 | history2 |
|------------------------------|------------|-------------------|----------|----------|
| Particles >4µm ASTM D7647 | | 10507 | --- | --- |
| Particles >6µm ASTM D7647 | >1300 | ▲ 2239 | --- | --- |
| Particles >14µm ASTM D7647 | >80 | ▲ 114 | --- | --- |
| Particles >21µm ASTM D7647 | >20 | ▲ 28 | --- | --- |
| Particles >38µm ASTM D7647 | >4 | 2 | --- | --- |
| Particles >71µm ASTM D7647 | >3 | 0 | --- | --- |
| Oil Cleanliness ISO 4406 (c) | >--/17/13 | ▲ 21/18/14 | --- | --- |

FLUID DEGRADATION

| method | limit/base | current | history1 | history2 |
|--------------------------------------|------------|-------------|----------|----------|
| Acid Number (AN) mg KOH/g ASTM D8045 | 1.0 | 0.47 | --- | --- |

OIL ANALYSIS REPORT







| VISUAL | method | limit/base | current | history1 | history2 |
|------------------|--------|------------|---------|--------------|----------|
| White Metal | scalar | *Visual | NONE | LIGHT | --- |
| Yellow Metal | scalar | *Visual | NONE | NONE | --- |
| Precipitate | scalar | *Visual | NONE | NONE | --- |
| Silt | scalar | *Visual | NONE | NONE | --- |
| Debris | scalar | *Visual | NONE | NONE | --- |
| Sand/Dirt | scalar | *Visual | NONE | NONE | --- |
| Appearance | scalar | *Visual | NORML | NORML | --- |
| Odor | scalar | *Visual | NORML | NORML | --- |
| Emulsified Water | scalar | *Visual | >0.05 | NEG | --- |
| Free Water | scalar | *Visual | | NEG | --- |

| FLUID PROPERTIES | method | limit/base | current | history1 | history2 |
|------------------|--------|------------|---------|-------------|----------|
| Visc @ 40°C | cSt | ASTM D445 | 45 | 51.8 | --- |

| SAMPLE IMAGES | method | limit/base | current | history1 | history2 |
|---------------|--------|------------|---------|----------|----------|
|---------------|--------|------------|---------|----------|----------|

| | | | |
|--------|--|----------|----------|
| Color | | no image | no image |
| Bottom | | no image | no image |

GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : KCPA009295 **Received** : 01 Feb 2024
Lab Number : 06076897 **Diagnosed** : 02 Feb 2024
Unique Number : 10858988 **Diagnostician** : Don Baldrige
Test Package : IND 2 (Additional Tests: KF, PrtCount)

PRESTONE
 19500 MARINER AVE
 TORRANCE, CA
 US 90503
 Contact: Service Manager

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)