




OIL ANALYSIS REPORT

Sample Rating Trend



ISO



Machine Id
KAESER DSD 200 9069048 (S/N 1192)

Component
Compressor

Fluid
KAESER SIGMA (OEM) S-460 (--- QTS)

DIAGNOSIS

▲ Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

▲ Contamination

There is a high amount of particulates present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			KC121644	KC111634	---
Sample Date	Client Info			11 Jan 2024	05 Oct 2023	---
Machine Age	hrs	Client Info		4827	2858	---
Oil Age	hrs	Client Info		0	2858	---
Oil Changed	Client Info			N/A	Changed	---
Sample Status				ABNORMAL	NORMAL	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1	0	---
Chromium	ppm	ASTM D5185m	>10	0	0	---
Nickel	ppm	ASTM D5185m	>3	<1	<1	---
Titanium	ppm	ASTM D5185m	>3	0	0	---
Silver	ppm	ASTM D5185m	>2	<1	0	---
Aluminum	ppm	ASTM D5185m	>10	5	11	---
Lead	ppm	ASTM D5185m	>10	3	<1	---
Copper	ppm	ASTM D5185m	>50	2	0	---
Tin	ppm	ASTM D5185m	>10	<1	<1	---
Vanadium	ppm	ASTM D5185m		0	<1	---
Cadmium	ppm	ASTM D5185m		0	0	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	---
Barium	ppm	ASTM D5185m	90	0	0	---
Molybdenum	ppm	ASTM D5185m		<1	0	---
Manganese	ppm	ASTM D5185m		2	0	---
Magnesium	ppm	ASTM D5185m	90	9	2	---
Calcium	ppm	ASTM D5185m	2	1	1	---
Phosphorus	ppm	ASTM D5185m		14	26	---
Zinc	ppm	ASTM D5185m		0	<1	---


CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	1	0	---
Sodium	ppm	ASTM D5185m		6	0	---
Potassium	ppm	ASTM D5185m	>20	4	2	---
Water	%	ASTM D6304	>0.05	0.005	0.002	---
ppm Water	ppm	ASTM D6304	>500	59	24.0	---

FLUID CLEANLINESS		method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		6465	2695	---
Particles >6µm		ASTM D7647	>1300	▲ 2369	585	---
Particles >14µm		ASTM D7647	>80	▲ 250	33	---
Particles >21µm		ASTM D7647	>20	▲ 65	8	---
Particles >38µm		ASTM D7647	>4	2	0	---
Particles >71µm		ASTM D7647	>3	0	0	---
Oil Cleanliness		ISO 4406 (c)	>--/17/13	▲ 20/18/15	19/16/12	---


FLUID DEGRADATION		method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.4	0.40	0.41	---

OIL ANALYSIS REPORT


▲ Particle Trend




Water (KF)




Acid Number



Water (KF)



Viscosity @ 40°C



VISUAL	method	limit/base	current	history1	history2	
White Metal	scalar	*Visual	NONE	LIGHT	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	---
Free Water	scalar	*Visual		NEG	NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 40°C	cSt	ASTM D445	46	45.8	48.1	---

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------

Color



Bottom




GRAPHS

Ferrous Alloys




Non-ferrous Metals



Viscosity @ 40°C



▲ Particle Count



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : KC121644
 Lab Number : 06077697
 Unique Number : 10859788
 Test Package : IND 2

CEMEX - FAIRBORN CEMENT
 3250 LINEBAUGH RD
 XENIA, OH
 US 45385
 Contact: SERVICE MANAGER

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
F: