

OIL ANALYSIS REPORT

Area CS-46 [PM12-2392716] Machine Id ATLAS COPCO ITJ207502 - MERCED UNION HSD-LIVINGSTON HS Component

Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear


All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



Sample Rating Trend



NORMAL


SAMPLE INFORM		no otle e el	linoit/le e ere		biotemit	bioten 0
	MATION	method	limit/base		history1	history2
Sample Number		Client Info		UCH06097147	UCH05774913	
Sample Date		Client Info		12 Feb 2024	26 Jan 2023	
Machine Age	hrs	Client Info		2519	1199	
Oil Age	hrs	Client Info		1319	1199	
Oil Changed		Client Info		Not Changd	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINATION		method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	<1	2	
Chromium	ppm	ASTM D5185m	>5	0	0	
Nickel	ppm	ASTM D5185m		5	8	
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>15	1	0	
Lead	ppm	ASTM D5185m	>65	0	0	
Copper	ppm	ASTM D5185m	>65	1	4	
Tin	ppm	ASTM D5185m	>10	0	0	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	1.5	0	0	
Barium	ppm	ASTM D5185m	0	0	2	
Molybdenum	ppm	ASTM D5185m	0	0	0	
Manganese	ppm	ASTM D5185m	0.3	0	0	
Magnesium	ppm	ASTM D5185m	0	3	1	
Calcium	ppm	ASTM D5185m	0	0	0	
Phosphorus	ppm	ASTM D5185m	406	198	29	
Zinc	ppm	ASTM D5185m	0	33	14	
Sulfur	ppm	ASTM D5185m	1283	1299	193	
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>35	4	4	
Sodium	ppm	ASTM D5185m		0	1	
Potassium	ppm	ASTM D5185m	>20	<1	0	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.463	0.244	0.083	



Jan26/23

OIL ANALYSIS REPORT

VISUAL



	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
	Precipitate	scalar	*Visual	NONE	NONE	NONE	
	Silt	scalar	*Visual	NONE	NONE	NONE	
	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Feb 12/24	Appearance	scalar	*Visual	NORML	NORML	NORML	
Fer	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.1	NEG	NEG	
	Free Water	scalar	*Visual		NEG	NEG	
	FLUID PROPER	TIES	method	limit/base	current	history1	history2
	Visc @ 40°C	cSt	ASTM D445	47.9	45.0	44.1	
	SAMPLE IMAGE	S	method	limit/base	current	history1	history2
Feb1224 +	Color				a.		no image
	Bottom						no image
	GRAPHS						
	Ferrous Alloys						
	¹⁰ iron						
	6 - million nickel						
			and the second se	Manual Association			
	2						
	0						
	Jan 26/23			Feb12/24			
	,			Feb			
	Non-ferrous Meta	ls					
	10 copper						
	E • [
	음 ₄ 2						
	2						
	2			12/24			
	2 0 0 2 2 2 0 2 2 2 0 2 2 2 0 2 2 2 2 0 2			Feb12/24			
	Viscosity @ 40°C				Acid Number		
	2 0 0 2 2 2 0 2 2 2 0 2 2 2 0 2 2 2 2 0 2						
	Viscosity @ 40°C						
	Viscosity @ 40°C						
	Viscosity @ 40°C						
	Viscosity @ 40°C			(b)HO,0.4 (b)HO,0.4 (b)HO,0.4 (b) HO,0.7 (b) HO,0.7 (c)	Base 		
	Viscosity @ 40°C			(b)HO,0.4 (b)HO,0.4 (b)HO,0.4 (b) HO,0.7 (b) HO,0.7 (c)	Base 		
	Viscosity @ 40°C						
Laboratory	Viscosity @ 40°C	1 Madiso	n Ave., Cary	(0.5 0.6 0.0 9 0.0 4 0.0 9 0.0 9 0.0 9 0.0	Base 	CISCO A	JR SYSTEM
Sample No.	Viscosity @ 40°C	Recei	ved : 22	, NC 27513 Feb 2024	Base 		214 27TH S
Sample No. Lab Number	Viscosity @ 40°C	Recei Teste	ved : 22 d : 23	, NC 27513 Feb 2024 Feb 2024	0 Bese		NIR SYSTEM 214 27TH S AMENTO, C
Sample No. Lab Number Unique Number	Viscosity @ 40°C	Recei	ved : 22 d : 23	, NC 27513 Feb 2024	0 Bese	SACR	214 27TH 5 AMENTO, 0 US 958
Sample No. Lab Number	Viscosity @ 40°C Viscosity @ 40°C Viscosity @ 40°C	Recei Teste Diagn	ved : 22 d : 23 losed : 24	, NC 27513 Feb 2024 Feb 2024 - Dor	0 Bese		214 27TH 9 AMENTO, 0 US 958 Y FRKOVIO