

OIL ANALYSIS REPORT

VISION 8000 Machine Id HODGE 2208100015 - COMP 2

Component

Compressor

{not provided} (--- GAL)

Sample Rating Trend



Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UHC0000878		
Sample Date		Client Info		05 Jan 2024		
Machine Age	hrs	Client Info		3942		
Oil Age	hrs	Client Info		3019		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATION	V	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	3		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	1		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	<1		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		0		
Manganese	ppm	ASTM D5185m		0		
Magnesium	ppm	ASTM D5185m		0		
Calcium	ppm	ASTM D5185m		0		
Phosphorus	ppm	ASTM D5185m		406		
Zinc	ppm	ASTM D5185m		45		
Sulfur	ppm	ASTM D5185m		839		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	<1		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.58		



OIL ANALYSIS REPORT




VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERT	TES	method	limit/base	current	history1	history2


Visc @ 40°C	cSt	ASTM D445	46.7	


		,	,
Color		no image	no image
Bottom		no image	no image

SAMPLE IMAGES



		Non-ferrous Metals
	¹⁰ T	
	8	copper
	۲Ţ	peaceassasse ESC
mdc	6-	nonnonnonno tin
id	4	
	2	ļļ-
	0	
		Jan5/24









Certificate L2367

Laboratory Sample No.

: UHC0000878 Lab Number : 06097194 Unique Number : 10890047 Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 22 Feb 2024 **Tested**

: 23 Feb 2024 Diagnosed : 24 Feb 2024 - Don Baldridge ATLANTA AIR COMPRESSOR 123 MERCHANTS PARK DR

HOSCHTON, GA US 30548

Contact: Derik Bray

Derik@atlantaaircompressor.com T: (470)252-9952

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

F: x:

Contact/Location: Derik Bray - UCATLHOS