


# **OIL ANALYSIS REPORT**

# VISION 8000 **HODGE 2104050220 - GRG GAINESVILLE**

Component

Compressor

{not provided} (4 GAL)





### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the


### Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UHC0000834	UHC0000628	
Sample Date		Client Info		15 Jan 2024	01 Aug 2023	
Machine Age	hrs	Client Info		9011	0	
Oil Age	hrs	Client Info		2230	6143	
Oil Changed		Client Info		Not Changd	Changed	
Sample Status				NORMAL	NORMAL	
CONTAMINATION	V	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	5	11	
Chromium	ppm	ASTM D5185m	>10	0	0	
Nickel	ppm	ASTM D5185m		0	0	
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m		0	0	
Aluminum	ppm	ASTM D5185m	>25	1	0	
Lead	ppm	ASTM D5185m	>25	0	0	
Copper	ppm	ASTM D5185m	>50	3	2	
Tin	ppm	ASTM D5185m	>15	0	<1	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	
Barium	ppm	ASTM D5185m		0	4	
Molybdenum	ppm	ASTM D5185m		0	0	
Manganese	ppm	ASTM D5185m		0	1	
Magnesium	ppm	ASTM D5185m		4	55	
Calcium	ppm	ASTM D5185m		26	211	
Phosphorus	ppm	ASTM D5185m		373	557	
Zinc	ppm	ASTM D5185m		169	1148	
Sulfur	ppm	ASTM D5185m		1546	4024	
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	3	3	
Sodium	ppm	ASTM D5185m		17	53	
Potassium	ppm	ASTM D5185m	>20	5	9	
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.71	1.73	




# **OIL ANALYSIS REPORT**




VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
Precipitate	scalar	*Visual	NONE	NONE	NONE	
Silt	scalar	*Visual	NONE	NONE	NONE	
Debris	scalar	*Visual	NONE	LIGHT	NONE	
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Appearance	scalar	*Visual	NORML	NORML	NORML	
Odor	scalar	*Visual	NORML	NORML	NORML	
<b>Emulsified Water</b>	scalar	*Visual	>0.1	NEG	NEG	
Free Water	scalar	*Visual		NEG	NEG	
FLUID PROPERT	IES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		44.9	56.1	


SAMPLE IMAGES no image Color **Bottom** no image

### **GRAPHS**



	Non-ferrous Metals
	8 - copper lead
mdd	6
	2
	Aug1/23









Certificate L2367

Laboratory Sample No.

: UHC0000834 Lab Number : 06097203 Unique Number : 10890056 Test Package : IND 2

To discuss this sample report, contact Customer Service at 1-800-237-1369.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 22 Feb 2024 **Tested** 

: 23 Feb 2024 Diagnosed

: 24 Feb 2024 - Don Baldridge

ATLANTA AIR COMPRESSOR 123 MERCHANTS PARK DR

HOSCHTON, GA US 30548

Contact: Derik Bray

Derik@atlantaaircompressor.com T: (470)252-9952

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: x: