




OIL ANALYSIS REPORT

Sample Rating Trend



WATER



Machine Id
CARL_U2120 CARL_U2120_SS2120

Component
Drive End Seal Pot

Fluid
ROYAL PURPLE BARRIER FLUID FDA22 (--- GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a light concentration of water present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		RP0025826	RP0034100	RP0034084
Sample Date	Client Info		20 Feb 2024	15 Nov 2023	25 Sep 2023
Machine Age	hrs	Client Info	2358	2358	2358
Oil Age	hrs	Client Info	2358	2358	2358
Oil Changed	Client Info		N/A	N/A	N/A
Sample Status			ABNORMAL	NORMAL	NORMAL

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >20	0	---	0
Chromium	ppm	ASTM D5185m >20	0	---	0
Nickel	ppm	ASTM D5185m >20	0	---	<1
Titanium	ppm	ASTM D5185m	0	---	0
Silver	ppm	ASTM D5185m	0	---	0
Aluminum	ppm	ASTM D5185m >20	0	---	0
Lead	ppm	ASTM D5185m >20	0	---	0
Copper	ppm	ASTM D5185m >20	0	---	0
Tin	ppm	ASTM D5185m >20	0	---	0
Vanadium	ppm	ASTM D5185m	0	---	0
Cadmium	ppm	ASTM D5185m	0	---	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	---	0
Barium	ppm	ASTM D5185m	0	---	0
Molybdenum	ppm	ASTM D5185m	0	---	0
Manganese	ppm	ASTM D5185m	<1	---	0
Magnesium	ppm	ASTM D5185m	0	---	0
Calcium	ppm	ASTM D5185m	<1	---	0
Phosphorus	ppm	ASTM D5185m	0	---	<1
Zinc	ppm	ASTM D5185m	0	---	0

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >15	<1	---	<1
Sodium	ppm	ASTM D5185m	<1	---	0
Potassium	ppm	ASTM D5185m >20	0	---	0
Water	%	ASTM D6304 >0.05	▲ 0.062	0.008	0.049
ppm Water	ppm	ASTM D6304 >500	▲ 629	84	490




FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	---	0.056	0.042

VISUAL

	method	limit/base	current	history1	history2
White Metal	scalar	*Visual NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual NONE	NONE	NONE	NONE
Silt	scalar	*Visual NONE	NONE	NONE	NONE
Debris	scalar	*Visual NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual NONE	NONE	NONE	NONE
Appearance	scalar	*Visual NORML	NORML	NORML	NORML
Odor	scalar	*Visual NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual >0.05	NEG	NEG	0.2%
Free Water	scalar	*Visual	NEG	---	---

OIL ANALYSIS REPORT



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : RP0025826
Lab Number : 06097341
Unique Number : 10890194
Test Package : PLANT
Received : 22 Feb 2024
Tested : 26 Feb 2024
Diagnosed : 26 Feb 2024 - Jonathan Hester

ENERGY TRANSFER - CARLTON
 11500 FRESSNER ROAD
 CARLTON, MI
 US 48117
 Contact: SCOTT VERHELLE

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)


T: (313)580-0267

F:

FLUID PROPERTIES

method	limit/base	current	history1	history2
Visc @ 40°C	cSt ASTM D445 5.2	5.71	---	5.71

SAMPLE IMAGES



GRAPHS

