




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Area
FOUR MILE RIDGE [200005315]
 Machine Id
83303 SITE 13
 Component
Wind Turbine Gearbox
 Fluid
CASTROL OPTIGEAR SYNTHETIC X 320 (--- LTR)



DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		NX012357	NX004208	NX010428
Sample Date	Client Info		02 Nov 2023	29 Mar 2023	27 Oct 2022
Machine Age	hrs	Client Info	70020	63806	61275
Oil Age	hrs	Client Info	70020	63806	61275
Oil Changed	Client Info		Not Changed	Not Changd	Not Changed
Sample Status			NORMAL	NORMAL	NORMAL

WEAR METALS

	method	limit/base	current	history1	history2	
PQ	ASTM D8184	>80	30	18	20	
Iron	ppm	ASTM D5185m	>150	55	48	40
Chromium	ppm	ASTM D5185m	>5	<1	0	<1
Nickel	ppm	ASTM D5185m	>10	<1	0	0
Titanium	ppm	ASTM D5185m	>10	0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>10	6	<1	<1
Lead	ppm	ASTM D5185m	>20	0	0	<1
Copper	ppm	ASTM D5185m	>50	2	2	2
Tin	ppm	ASTM D5185m	>10	<1	0	<1
Vanadium	ppm	ASTM D5185m		<1	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0

ADDITIVES

	method	limit/base	current	history1	history2	
Boron	ppm	ASTM D5185m		29	0	46
Barium	ppm	ASTM D5185m		2	0	2
Molybdenum	ppm	ASTM D5185m	1150	773	736	722
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		8	10	7
Calcium	ppm	ASTM D5185m	2000	1548	1481	1461
Phosphorus	ppm	ASTM D5185m	400	358	341	324
Zinc	ppm	ASTM D5185m	0	0	0	2
Sulfur	ppm	ASTM D5185m	1850	1817	1671	1942

CONTAMINANTS

	method	limit/base	current	history1	history2	
Silicon	ppm	ASTM D5185m	>50	10	10	10
Sodium	ppm	ASTM D5185m	>20	9	9	9
Potassium	ppm	ASTM D5185m	>20	1	0	<1
Water	%	ASTM D6304	>0.05	0.018	0.007	0.027
ppm Water	ppm	ASTM D6304	>500	188	76.4	279.8

FLUID CLEANLINESS






	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647		338	682	379
Particles >6µm	ASTM D7647	>2500	67	102	126
Particles >14µm	ASTM D7647	>320	8	8	19
Particles >21µm	ASTM D7647	>80	3	1	6
Particles >38µm	ASTM D7647	>20	0	0	1
Particles >71µm	ASTM D7647	>4	0	0	0
Oil Cleanliness	ISO 4406 (c)	>--/18/15	16/13/10	17/14/10	16/14/11

FLUID DEGRADATION

	method	limit/base	current	history1	history2	
Acid Number (AN)	mg KOH/g	ASTM D8045	1.6	0.48	0.60	1.61




OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445 320	320	319	315

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : NX012357
 Lab Number : 06097720
 Unique Number : 10890573
 Test Package : IND 2 (Additional Tests: KF, PQ, PrtCount)

Received : 22 Feb 2024
 Tested : 23 Feb 2024
 Diagnosed : 25 Feb 2024 - Doug Bogart

NORDEX USA - Chicago
 300 SOUTH WACKER DRIVE, SUITE 1500
 CHICAGO, IL
 US 60606

Contact: DEVIN LINEHAN
 DLinehan@nordex-online.com

T: (312)386-4124
 F: (312)386-7102

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)