

OIL ANALYSIS REPORT


Sample Rating Trend

NORMAL

Refrigeration Compressor FRICK TYSLEX 0 FRK (S/N S02890)

Refrigeration Compressor

USPI 1009-68 SC (--- GAL)





DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the component. The amount and size of particulates present in the system is acceptable.


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.


		g2013 Oct20	14 Jan2016 Jun2017	Sep2018 Jan2020 Jun2021 \$	Sep 2022	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		USP0007795	USP243918	USP183529
Sample Date		Client Info		20 Feb 2024	17 Oct 2023	18 Jul 2023
Machine Age	hrs	Client Info		44822	41697	39604
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	ATTENTION
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>8	4	0	2
Chromium	ppm	ASTM D5185m	>2	0	0	0
Nickel	ppm	ASTM D5185m		0	<1	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>3	<1	<1	<1
Lead	ppm	ASTM D5185m	>2	0	<1	0
Copper	ppm	ASTM D5185m	>8	0	0	0
Tin	ppm	ASTM D5185m	>4	<1	<1	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		<1	<1	0
Magnesium	ppm	ASTM D5185m		<1	0	0
Calcium	ppm	ASTM D5185m		1	1	0
Phosphorus	ppm	ASTM D5185m		<1	0	0
Zinc	ppm	ASTM D5185m		0	0	0
Sulfur	ppm	ASTM D5185m	50	6	0	7
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	4	3	3
Sodium	ppm	ASTM D5185m		<1	<1	0
Potassium	ppm	ASTM D5185m	>20	<1	0	0
Water	%	ASTM D6304	>0.01	0.005	0.008	0.005
ppm Water	ppm	ASTM D6304	>100	51	85.6	59.0
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647	>10000	2455	2792	▲ 10342
Particles >6µm		ASTM D7647	>2500	379	537	▲ 2872
Particles >14μm		ASTM D7647	>320	16	18	140
Particles >21μm		ASTM D7647	>80	3	3	20
Particles >38μm		ASTM D7647	>20	0	0	0
Particles >71μm		ASTM D7647		0	0	0
Oil Cleanliness		ISO 4406 (c)	>20/18/15	18/16/11	19/16/11	2 1/19/14
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D974	0.005	0.015	0.014	0.014





OIL ANALYSIS REPORT




20k	•••••• 6j.	m m um	Λ				1
10k - Abn	ormal		A	Λ	1	1	Ax
0k	A		4	\ \ \ \	**	V	M
Aug1/13	0ct10/14	Jan21/16	Jun6/17	Sep18/18	Jan17/20	Jun3/21	Sep19/22










Color		
Bottom		









Laboratory Sample No. Lab Number Unique Number: 10895995

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : USP0007795 : 06097765

Received **Tested**

: 22 Feb 2024

: 25 Feb 2024 : 25 Feb 2024 - Doug Bogart Diagnosed

TYSON-LEXINGTON-USP - MAIN PLANT PO BOX 920, PROSPECT ROAD US 283

LEXINGTON, NE US 68850

Contact: SCOTT NIERMAN

Test Package : IND 2 Certificate L2367 To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T: (308)324-8221

F: (308)324-8233