


Area [1910261]

OIL ANALYSIS REPORT

NH3 COMP 3 (S/N S0424KFMPTHAA3)

Refrigeration Compressor

ARO 717 HT (--- GAL)





Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the

Fluid Condition


The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0881652	WC0850530	WC0799600
Sample Date		Client Info		11 Feb 2024	11 Nov 2023	16 Aug 2023
Machine Age	hrs	Client Info		93160	93044	92592
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>8	0	0	<1
Chromium	ppm	ASTM D5185m	>2	0	0	0
Nickel	ppm	ASTM D5185m		<1	0	0
Titanium	ppm	ASTM D5185m		0	0	<1
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>3	0	0	0
Lead	ppm	ASTM D5185m	>2	0	0	0
Copper	ppm	ASTM D5185m	>8	0	0	0
Tin	ppm	ASTM D5185m	>4	<1	0	0
Vanadium	ppm	ASTM D5185m		0	0	<1
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		0	0	0
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		0	0	0
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		<1	0	<1
Calcium	ppm	ASTM D5185m		<1	0	0
Phosphorus	ppm	ASTM D5185m		<1	2	2
Zinc	ppm	ASTM D5185m		0	0	0
Sulfur	ppm	ASTM D5185m		0	0	0
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	<1	0	<1
Sodium	ppm	ASTM D5185m		<1	<1	0
Potassium	ppm	ASTM D5185m	>20	<1	0	<1
Water	%	ASTM D6304	>0.01	0.002	0.001	0.001
ppm Water	ppm	ASTM D6304	>100	16	14	4.7
FLUID DEGRADA	TION	method	limit/base	current	history1	history2




Water (KF)


OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.01	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
FLUID PROPERT	TES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		64.7	63.9	64.4
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color						
Bottom						















Certificate L2367

Report Id: LEPLEM01 [WUSCAR] 06097795 (Generated: 02/25/2024 22:03:28) Rev: 1

Laboratory Sample No. Lab Number : 06097795

Test Package : IND 2

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0881652

To discuss this sample report, contact Customer Service at 1-800-237-1369.

Received Unique Number : 10896025

Tested Diagnosed

: 22 Feb 2024 : 25 Feb 2024 : 25 Feb 2024 - Doug Bogart

LEPRINO FOODS - LEMOORE EAST 490 F ST.

LEMOORE, CA US 93245

Contact: CHRISTOPHER FOGG

cfogg@leprinofoods.com T: (559)925-7137

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: CHRISTOPHER FOGG - LEPLEM01

F: