


OIL ANALYSIS REPORT

ÎR ULTRA COOLANT [1403790] **INGERSOLL RAND CBV695025 - PITNEY BOWES**

Component

Compressor





Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the


Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORM	//ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCH06098527		
Sample Date		Client Info		28 Dec 2023		
Machine Age	hrs	Client Info		16727		
Oil Age	hrs	Client Info		16727		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATIO	V	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m	. 10	<1		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	<1		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	<1		
Tin	ppm	ASTM D5185m	>15	<1		
Vanadium	ppm	ASTM D5185m	710	0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0		
Barium	ppm	ASTM D5185m	500	320		
Molybdenum	ppm	ASTM D5185m	0	0		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m	0	2		
Calcium	ppm	ASTM D5185m	0	3		
Phosphorus	ppm	ASTM D5185m	20	1		
Zinc	ppm	ASTM D5185m	0	6		
Sulfur	ppm	ASTM D5185m	200	306		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	4		
Sodium	ppm	ASTM D5185m		62		
Potassium	ppm	ASTM D5185m	>20	6		
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045		0.25		



OIL ANALYSIS REPORT




VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.1	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERT	ΓIES	method	limit/base	current	history1	history2

SAMPLE IMAGES	method	limit/base	current	history1	history2
Color				no image	no image
Bottom				no image	no image

52.9

GRAPHS


Visc @ 40°C




cSt

ASTM D445 49.4

	Non-rerrous M	etais				
	10 _T					
	copper					
	bean assessesses					
_	6 + ********* tin					
ppm						
	4					
	2					
	() 	*******	***********	***************************************	***************************************	
	733					Jec28/23
)ec28/23					28
	39					9
	_					
	Viscosity @ 40	°C				









Certificate L2367

Laboratory Sample No.

: WearCheck USA - 501 Madison Ave., Cary, NC 27513

Lab Number : 06098527 Unique Number: 10896757 Test Package : IND 2

: UCH06098527

Received : 23 Feb 2024 **Tested** Diagnosed

: 26 Feb 2024 : 26 Feb 2024 - Don Baldridge **AIR TECHNOLOGIES INC (MID)**

400 WRIGHT AVE MIDDLETOWN, OH US 45044

Contact: Josh Oaks

F: (513)539-6040

josh.oaks@aircompressors.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)