


OIL ANALYSIS REPORT



DIRT



Machine Id 49 Component **Diesel Engine** SHELL ROTELLA T 15W40 (--- GAL)

DIAGNOSIS

Recommendation

We advise that you check the air filter, air induction system, and any areas where dirt may enter the component. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

Fuel content negligible. Elemental levels of silicon (Si) and aluminum (Al) indicate alumina-silicate (coarse dirt) ingress. Elevated aluminum (AI) and/or lead (Pb) and potassium (K) levels in your metals analysis are likely a result of solder flux release into the lubricant and is common on new equipment/components.


Fluid Condition

The oil viscosity is lower than normal. The BN result indicates that there is suitable alkalinity remaining in the oil. Confirm oil type.

| SAMPLE INFORM | ATION | method | limit/base | current | history1 | history2 |
|----------------------------------------------------------------------------------------|-------------------------------------------------|------------------------------------------------------------------------------------------------------|---------------------------------------------|---------------------------------------------------------|----------------------------------------------------------|----------------------|
| Sample Number | | Client Info | | WC0867905 | WC0740553 | |
| Sample Date | | Client Info | | 22 Feb 2024 | 22 May 2023 | |
| Machine Age | mls | Client Info | | 0 | 0 | |
| Oil Age | mls | Client Info | | 0 | 0 | |
| Oil Changed | | Client Info | | N/A | N/A | |
| Sample Status | | | | ABNORMAL | NORMAL | |
| CONTAMINATIO | N | method | limit/base | current | history1 | history2 |
| Water | | WC Method | >0.2 | NEG | NEG | |
| WEAR METALS | | method | limit/base | current | history1 | history2 |
| Iron | ppm | ASTM D5185m | >100 | 34 | 26 | |
| Chromium | ppm | ASTM D5185m | >20 | 1 | <1 | |
| Nickel | ppm | ASTM D5185m | >4 | 0 | 0 | |
| Titanium | ppm | ASTM D5185m | | <1 | 0 | |
| Silver | ppm | ASTM D5185m | >3 | 0 | 0 | |
| Aluminum | ppm | ASTM D5185m | >20 | 1 5 | 5 | |
| Lead | ppm | ASTM D5185m | >40 | <1 | 0 | |
| Copper | ppm | ASTM D5185m | >330 | 56 | <1 | |
| Tin | ppm | ASTM D5185m | >15 | <1 | 0 | |
| Vanadium | ppm | ASTM D5185m | | 0 | 0 | |
| Cadmium | ppm | ASTM D5185m | | 0 | 0 | |
| ADDITIVES | | method | limit/base | current | history1 | history2 |
| Boron | ppm | ASTM D5185m | 316 | 36 | 13 | |
| Barium | ppm | ASTM D5185m | 0.0 | 5 | 0 | |
| Molybdenum | ppm | ASTM D5185m | 1.2 | 44 | 64 | |
| Manganese | ppm | ASTM D5185m | | 5 | <1 | |
| Magnesium | ppm | ASTM D5185m | 24 | 802 | 768 | |
| Calcium | ppm | ASTM D5185m | 2292 | 1230 | 1325 | |
| Phosphorus | ppm | ASTM D5185m | 1064 | 697 | 1038 | |
| Zinc | ppm | ASTM D5185m | 1160 | 859 | 1270 | |
| Sulfur | ppm | ASTM D5185m | 4996 | 2326 | 3907 | |
| CONTAMINANTS | | method | limit/base | current | history1 | history2 |
| Silicon | | | | | | |
| Chicon | ppm | ASTM D5185m | >25 | ^ 27 | 4 | |
| Sodium | ppm ppm | ASTM D5185m ASTM D5185m | >25 | ▲ 27 7 | 4 <1 | |
| Sodium Potassium | ppm ppm | | >25 >20 | | <1 2 | |
| Sodium | ppm | ASTM D5185m | | 7 | <1 | |
| Sodium Potassium | ppm ppm | ASTM D5185m ASTM D5185m | >20 >5 | 7 61 | <1 2 | |
| Sodium Potassium Fuel | ppm ppm % % | ASTM D5185m ASTM D5185m ASTM D3524 | >20 | 7 61 1.7 NEG current | <1 2 <1.0 NEG history1 | |
| Sodium Potassium Fuel Glycol INFRA-RED Soot % | ppm ppm % | ASTM D5185m ASTM D5185m ASTM D3524 *ASTM D2982 method *ASTM D7844 | >20 >5 | 7 61 1.7 NEG current 0.3 | <1 2 <1.0 NEG | |
| Sodium Potassium Fuel Glycol INFRA-RED | ppm ppm % % | ASTM D5185m ASTM D5185m ASTM D3524 *ASTM D2982 method *ASTM D7844 *ASTM D7624 | >20 >5 limit/base | 7 61 1.7 NEG current | <1 2 <1.0 NEG history1 | history2 |
| Sodium Potassium Fuel Glycol INFRA-RED Soot % | ppm ppm % % | ASTM D5185m ASTM D5185m ASTM D3524 *ASTM D2982 method *ASTM D7844 | >20 >5 limit/base >3 | 7 61 1.7 NEG current 0.3 | <1 2 <1.0 NEG history1 0.6 | history2 |
| Sodium Potassium Fuel Glycol INFRA-RED Soot % Nitration | ppm ppm % % % Abs/cm Abs/.1mm | ASTM D5185m ASTM D5185m ASTM D3524 *ASTM D2982 method *ASTM D7844 *ASTM D7624 | >20 >5 limit/base >3 >20 | 7 61 1.7 NEG current 0.3 10.1 | <1 2 <1.0 NEG history1 0.6 7.3 | history2 |
| Sodium Potassium Fuel Glycol INFRA-RED Soot % Nitration Sulfation | ppm ppm % % % Abs/cm Abs/.1mm | ASTM D5185m ASTM D5185m ASTM D3524 *ASTM D2982 *ASTM D7844 *ASTM D7624 *ASTM D7415 | >20 >5 limit/base >3 >20 >30 | 7 61 1.7 NEG current 0.3 10.1 20.5 | <1 2 <1.0 NEG history1 0.6 7.3 19.0 | history2 |



OIL ANALYSIS REPORT



Contact/Location: MATT POWELL - ANSWAD

T:

F: