




OIL ANALYSIS REPORT

Sample Rating Trend

NORMAL



Machine Id
6012514
 Component
Diesel Engine
 Fluid
{not provided} (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			IL0034871	IL06019341	IL05261807
Sample Date	Client Info			14 Feb 2024	25 Sep 2023	26 Jan 2021
Machine Age	mls	Client Info		11345	10547	4406
Oil Age	mls	Client Info		0	10547	4406
Oil Changed	Client Info			N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Water	WC Method	>0.2		NEG	NEG	NEG
Glycol	WC Method			NEG	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	77	54	53
Chromium	ppm	ASTM D5185m	>20	2	<1	<1
Nickel	ppm	ASTM D5185m	>4	1	0	<1
Titanium	ppm	ASTM D5185m		<1	0	<1
Silver	ppm	ASTM D5185m	>3	0	0	0
Aluminum	ppm	ASTM D5185m	>20	18	14	7
Lead	ppm	ASTM D5185m	>40	<1	<1	<1
Copper	ppm	ASTM D5185m	>330	15	11	56
Tin	ppm	ASTM D5185m	>15	<1	<1	<1
Antimony	ppm	ASTM D5185m		---	---	0
Vanadium	ppm	ASTM D5185m		<1	<1	0
Cadmium	ppm	ASTM D5185m		<1	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		25	30	38
Barium	ppm	ASTM D5185m		34	0	4
Molybdenum	ppm	ASTM D5185m		16	19	40
Manganese	ppm	ASTM D5185m		2	1	3
Magnesium	ppm	ASTM D5185m		570	611	495
Calcium	ppm	ASTM D5185m		1143	1381	1334
Phosphorus	ppm	ASTM D5185m		611	725	760
Zinc	ppm	ASTM D5185m		775	814	987
Sulfur	ppm	ASTM D5185m		2756	2681	2212




CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	13	11	24
Sodium	ppm	ASTM D5185m		4	3	7
Potassium	ppm	ASTM D5185m	>20	50	41	31
Fuel	%	ASTM D3524	>5	<1.0	<1.0	<1.0

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0.8	0.6	0.8
Nitration	Abs/cm	*ASTM D7624	>20	10.8	10.8	12.7
Sulfation	Abs/.1mm	*ASTM D7415	>30	24.7	24.0	26.4

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	16.6	17.0	22.6
Base Number (BN)	mg KOH/g	ASTM D2896		5.0	6.4	6.9







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.2	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	11.0	11.0	12.5

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : IL0034871 **Received** : 26 Feb 2024
Lab Number : **06099915** **Tested** : 27 Feb 2024
Unique Number : 10898145 **Diagnosed** : 28 Feb 2024 - Jonathan Hester
Test Package : FLEET (Additional Tests: FuelDilution)

IDEALRELEASE OF ATLANTA - FULTON
 4675 BAKERS FERRY ROAD
 ATLANTA, GA
 US 30331
 Contact: DAVID JOHNS
 davidjohns@idealease.com
 T: (404)699-5571
 F: (404)699-7420

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)