

# **OIL ANALYSIS REPORT**

### Sample Rating Trend



# SOUTHWEST DETROIT - 3005676058

Component

**Diesel Engine** 

NAPA 5W30 (--- GAL)

### Recommendation

Resample at the next service interval to monitor.

All component wear rates are normal.

#### Contamination

There is no indication of any contamination in the


### **Fluid Condition**

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is acceptable for the time in service.

		Feb	2022	Feb 2023 Feb 20	D24	
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0894425	WC0771553	WC0637068
Sample Date		Client Info		21 Feb 2024	07 Feb 2023	10 Feb 2022
Machine Age	hrs	Client Info		100	70	42
Oil Age	hrs	Client Info		22	23	20
Oil Changed		Client Info		Not Changd	Not Changd	Not Changd
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATIO	N	method	limit/base	current	history1	history2
Fuel		WC Method	>3.0	<1.0	<1.0	<1.0
Water		WC Method	>0.2	NEG	NEG	NEG
Glycol		WC Method		NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>200	0	<1	4
Chromium	ppm	ASTM D5185m	>20	0	<1	0
Nickel	ppm	ASTM D5185m	>2	0	0	0
Titanium	ppm	ASTM D5185m	>2	<1	<1	0
Silver	ppm	ASTM D5185m	>2	0	0	0
Aluminum	ppm	ASTM D5185m	>30	<1	0	15
Lead	ppm	ASTM D5185m	>30	0	0	<1
Copper	ppm	ASTM D5185m	>30	<1	0	2
Tin	ppm	ASTM D5185m	>15	0	0	0
Antimony	ppm	ASTM D5185m				0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		146	175	104
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		54	46	7
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m		483	419	706
Calcium	ppm	ASTM D5185m		1057	1048	1402
Phosphorus	ppm	ASTM D5185m		657	627	687
Zinc	ppm	ASTM D5185m		746	761	771
Sulfur	ppm	ASTM D5185m		2928	2776	2579
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>30	30	27	16
Sodium	ppm	ASTM D5185m		<1	5	4
Potassium	ppm	ASTM D5185m	>20	2	1	2
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0	0.1	0.1
Nitration	Abs/cm	*ASTM D7624	>20	4.1	4.5	7.2
Sulfation	Abs/.1mm	*ASTM D7415	>30	13.7	14.1	19.9
FLUID DEGRADA	ATION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	6.7	7.1	15.3
Base Number (BN)	mg KOH/g	ASTM D2896	-	6.3	6.8	8.6
(511)					0	



## **OIL ANALYSIS REPORT**



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	LIGHT
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG	NEG
ELLID DDODEDI	TIEC	mathad	limit/bass	ourront.	hiotomit	hiotom/2

Viscosity @ 1	.00°C	
14T		
13 - Abnormal		
12		
(3,001)		
₹ 10 -		
Abnormal		
9+		
52 ± 8	- 53	V.
eb10/2	Feb 7/23	F217
2	-	ů.

Visc @ 100°C	cSt	ASTM D445	10.3	10.6	11.1
GRAPHS					
Iron (ppm)			Lead (ppm)	)	
Severe		i	Severe		
Abnormal			E 40		
100+			Abnormal		
0			0		
Feb 10/22	Feb7/23	Feb21/24	Feb 10/22	Feb7/23	Feb21/24
ے Aluminum (ppm)		2	۳ Chromium		Ξ.
Severe			50	(LE)	
Abnormal			40 7		
and Abnormal			Abnormal		
10			10-		
- Feb 10/22	Feb7/23 -	Feb21/24	- Ceb 10/22 - T	Feb7/23	Feb21/24
	量	Feb2			Feb2
Copper (ppm)			Silicon (ppr	n)	
50			40		
Abnormal			Abnormal		
10+			10		
0	- 23	55			
Feb10/22	Feb7/23	Feb21/24.	Feb10/22	Feb7/23	Feb21/24
Viscosity @ 100°	С		Base Numb	er	
14 13 Abnormal			0.00 8.0		
© 12 © 11 © 10 Abnormal			g 6.0		
Abitotitia			8.00		
8			2.0		
Feb 10/22	Feb7/23 -	Feb21/24	Feb 10/22	Feb7/23	Feb21/24
Œ	_	2	Œ.	_	2





Laboratory

**Sample No.** : WC0894425

Lab Number : 06101325 Unique Number : 10899555

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 27 Feb 2024 Tested : 28 Feb 2024

Diagnosed : 28 Feb 2024 - Don Baldridge Test Package: MOB 1 (Additional Tests: TBN)

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

**NATIONAL POWER CORP** 

4541 PRESLYN DR RALEIGH, NC US 27616

Contact: BRANDON RICE brandon.rice@natpow.com

T:

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Contact/Location: BRANDON RICE - NATRAL

F: (919)790-9714