<u>Sullivan</u> Palatek.

OIL ANALYSIS REPORT

PALEXTRA 44 Machine Id SULLIVAN PALATEK 23CE003822 - MSP Component

Compressor

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.



Sample Rating Trend




NORMAL

SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		UCS06101761		
Sample Date		Client Info		22 Feb 2024		
Machine Age	hrs	Client Info		2095		
Oil Age	hrs	Client Info		2095		
Oil Changed		Client Info		Not Changd		
Sample Status				NORMAL		
CONTAMINATIO	N	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	0		
Chromium	ppm	ASTM D5185m	>10	0		
Nickel	ppm	ASTM D5185m		0		
Titanium	ppm	ASTM D5185m		0		
Silver	ppm	ASTM D5185m		0		
Aluminum	ppm	ASTM D5185m	>25	0		
Lead	ppm	ASTM D5185m	>25	0		
Copper	ppm	ASTM D5185m	>50	<1		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m		0		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0		
Barium	ppm	ASTM D5185m	0.3	0		
Molybdenum	ppm	ASTM D5185m	0	0		
Manganese	ppm	ASTM D5185m	0.3	0		
Magnesium	ppm	ASTM D5185m	0.4	0		
Calcium	ppm	ASTM D5185m	0	0		
Phosphorus	ppm	ASTM D5185m	689	601		
Zinc	ppm	ASTM D5185m	0	0		
Sulfur	ppm	ASTM D5185m	1237	917		
CONTAMINANTS	;	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6		
Sodium	ppm	ASTM D5185m		0		
Potassium	ppm	ASTM D5185m	>20	0		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	0.135	0.20		



OIL ANALYSIS REPORT

VISUAL



	VISUAL		method	limit/base	current	history1	history2	
	White Metal	scalar	*Visual	NONE	NONE			
	Yellow Metal	scalar	*Visual	NONE	NONE			
	Precipitate	scalar	*Visual	NONE	NONE			
	Silt	scalar	*Visual	NONE	NONE			
	Debris	scalar	*Visual	NONE	NONE			
	Sand/Dirt	scalar	*Visual	NONE	NONE			
Feb 22/24	Appearance	scalar	*Visual	NORML	NORML			
Febő	Odor	scalar	*Visual	NORML	NORML			
	Emulsified Water	scalar	*Visual	>0.1	NEG			
	Free Water	scalar	*Visual		NEG			
	FLUID PROPERT	TIES	method	limit/base	current	history1	history2	
	Visc @ 40°C	cSt	ASTM D445	44.62	42.8			
	_							
	SAMPLE IMAGES	5	method	limit/base	current	history1	history2	
Feb 22/24 +	Color				a. 0.	no image	no image	
	Bottom					no image	no image	
	Non-ferrous Metal	5		4 Feb22/24				
	Viscosity @ 40°C			Feb22224 51.0 01.0 000 Acid Number (mg K0H/g) 5000 Acid Number (mg	Acid Number			
Laboratory Sample No. Lab Number Unique Number Test Package	: WearCheck USA - 50 : UCS06101761 : 06101761 : 10899991 : IND 2	Recei Teste Diagr	Madison Ave., Cary, NC 27513 Received : 27 Feb 2024 Tested : 28 Feb 2024 Diagnosed : 29 Feb 2024 - Don Baldridge re at 1-800-237-1369. 025 scope of accreditation.			TRI-STATE AIR COMPRESSO 10635 RAPP R MIDDLETOWN, O US 4444 Contact tristateaircompressor@gmail.cor T: (330)717-650		