


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



PIERCE ENGINE 16 - 6580

Component

Hydraulic System

AW HYDRAULIC OIL ISO 46 (--- GAL)

Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The condition of the oil is acceptable for the time in service.

		Aug201	8 Feb 2022	Jan 2023	Feb 2024	
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0890659	WC0762406	WC0658076
Sample Date		Client Info		24 Feb 2024	23 Jan 2023	03 Feb 2022
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	Not Changd	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATIO	Ν	method	limit/base	current	history1	history2
Water		WC Method	>0.1	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	0	1	1
Chromium	ppm	ASTM D5185m	>10	0	<1	<1
Nickel	ppm	ASTM D5185m	>10	0	0	0
Titanium	ppm	ASTM D5185m		0	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>10	0	1	<1
Lead	ppm	ASTM D5185m	>10	0	0	0
Copper	ppm	ASTM D5185m	>75	2	3	3
Tin	ppm	ASTM D5185m	>10	0	0	0
Antimony	ppm	ASTM D5185m				0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	5	0	0	<1
Barium	ppm	ASTM D5185m	5	0	0	0
Molybdenum	ppm	ASTM D5185m	5	0	<1	<1
Manganese	ppm	ASTM D5185m		0	0	0
Magnesium	ppm	ASTM D5185m	25	0	<1	0
Calcium	ppm	ASTM D5185m	200	60	64	67
Phosphorus	ppm	ASTM D5185m	300	397	422	450
Zinc	ppm	ASTM D5185m	370	507	555	556
Sulfur	ppm	ASTM D5185m	2500	2951	3309	2503
CONTAMINANTS	3	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>20	2	2	3
Sodium	ppm	ASTM D5185m		<1	<1	<1
Potassium	ppm	ASTM D5185m	>20	4	0	0
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	VLITE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	VLITE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
		** (*)	NODAN		NODA	NOBM

NORML

NORML

>0.1

NORML

NORML

NEG

NEG

NORML

NORML

NEG

Odor

Appearance

Emulsified Water

scalar

scalar

*Visual

*Visual

scalar *Visual

scalar *Visual

NORML


NORML

NEG


Subjected By: RANDEGPRICE




OIL ANALYSIS REPORT



FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	51.3	53.4	51.0
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image



Non-ferrous Metals Viscosity @ 40°C





Laboratory Sample No.

Lab Number : 06121266 Unique Number : 10930099 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 : WC0890659

Received Tested

: 18 Mar 2024 : 19 Mar 2024 Diagnosed

: 19 Mar 2024 - Wes Davis

GREENVILLE FIRE DEPARTMENT PO BOX 7207 GREENVILLE, NC US 27835

Contact: JESSE HARRIS jjharris@greenvillenc.gov T: (252)933-2200

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Submitted By: RANDY PRICE