




# OIL ANALYSIS REPORT

Sample Rating Trend

**NORMAL**



Area  
**SCHTRUCK**  
 Machine Id  
**6273 [SCHTRUCK]**

Component  
**Diesel Engine**  
 Fluid  
**PETRO CANADA DURON SHP 15W40 (--- GAL)**

## DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor.

### Wear

All component wear rates are normal.

### Contamination

There is no indication of any contamination in the oil.

### Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			<b>SBP0006996</b>	SBP0004169	---
Sample Date	Client Info			<b>12 Mar 2024</b>	15 Mar 2023	---
Machine Age	mls	Client Info		<b>463170</b>	434558	---
Oil Age	mls	Client Info		<b>28612</b>	39782	---
Oil Changed	Client Info			<b>Changed</b>	Changed	---
Sample Status				<b>NORMAL</b>	NORMAL	---

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method	>6.0		<b>&lt;1.0</b>	<1.0	---
Water	WC Method	>0.2		<b>NEG</b>	NEG	---
Glycol	WC Method			<b>NEG</b>	NEG	---

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	<b>21</b>	28	---
Chromium	ppm	ASTM D5185m	>20	<b>1</b>	1	---
Nickel	ppm	ASTM D5185m	>2	<b>&lt;1</b>	1	---
Titanium	ppm	ASTM D5185m		<b>0</b>	<1	---
Silver	ppm	ASTM D5185m	>2	<b>0</b>	0	---
Aluminum	ppm	ASTM D5185m	>25	<b>17</b>	19	---
Lead	ppm	ASTM D5185m	>40	<b>1</b>	3	---
Copper	ppm	ASTM D5185m	>330	<b>2</b>	2	---
Tin	ppm	ASTM D5185m	>15	<b>&lt;1</b>	<1	---
Vanadium	ppm	ASTM D5185m		<b>0</b>	0	---
Cadmium	ppm	ASTM D5185m		<b>0</b>	0	---

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	<b>1</b>	17	---
Barium	ppm	ASTM D5185m	0	<b>0</b>	2	---
Molybdenum	ppm	ASTM D5185m	60	<b>65</b>	56	---
Manganese	ppm	ASTM D5185m	0	<b>&lt;1</b>	<1	---
Magnesium	ppm	ASTM D5185m	1010	<b>1016</b>	546	---
Calcium	ppm	ASTM D5185m	1070	<b>1196</b>	1774	---
Phosphorus	ppm	ASTM D5185m	1150	<b>1104</b>	798	---
Zinc	ppm	ASTM D5185m	1270	<b>1301</b>	1005	---
Sulfur	ppm	ASTM D5185m	2060	<b>3124</b>	2162	---



CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<b>8</b>	6	---
Sodium	ppm	ASTM D5185m		<b>6</b>	2	---
Potassium	ppm	ASTM D5185m	>20	<b>2</b>	4	---

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	<b>0.3</b>	0.5	---
Nitration	Abs/cm	*ASTM D7624	>20	<b>9.7</b>	11.2	---
Sulfation	Abs/.1mm	*ASTM D7415	>30	<b>20.6</b>	23.8	---

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	<b>18.1</b>	23.8	---
Base Number (BN)	mg KOH/g	ASTM D2896	9.8	<b>6.2</b>	6.9	---







# OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	---
Yellow Metal	scalar	*Visual	NONE	NONE	---
Precipitate	scalar	*Visual	NONE	NONE	---
Silt	scalar	*Visual	NONE	NONE	---
Debris	scalar	*Visual	NONE	NONE	---
Sand/Dirt	scalar	*Visual	NONE	NONE	---
Appearance	scalar	*Visual	NORML	NORML	---
Odor	scalar	*Visual	NORML	NORML	---
Emulsified Water	scalar	*Visual	>0.2	NEG	---
Free Water	scalar	*Visual		NEG	---

FLUID PROPERTIES	method	limit/base	current	history1	history2	
Visc @ 100°C	cSt	ASTM D445	15.4	<b>13.6</b>	12.8	---

## GRAPHS



Certificate L2367

**Laboratory** : WearCheck USA - 501 Madison Ave., Cary, NC 27513  
**Sample No.** : SBP0006996  
**Lab Number** : **06121442**  
**Unique Number** : 10930275  
**Test Package** : FLEET

**Received** : 18 Mar 2024  
**Tested** : 19 Mar 2024  
**Diagnosed** : 19 Mar 2024 - Wes Davis

**SCHMIDT TRANSPORTATION - 605449**  
 108 E Bay Road  
 Plattsmouth, NE  
 US 68048  
 Contact: NICK DOTY  
 doty@liquidtrucking.com  
 T: (402)949-9398  
 F:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

\* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)