




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
SANDY LOU

Component
Starboard Genset

Fluid
CHEVRON DELO 400 SDE SAE 15W40 (3 GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION		method	limit/base	current	history1	history2
Sample Number	Client Info			MW0047380	MW0047397	MW0047389
Sample Date	Client Info			13 Mar 2024	30 Jan 2024	28 Nov 2023
Machine Age	hrs	Client Info		32035	26389	25838
Oil Age	hrs	Client Info		208	551	286
Oil Changed	Client Info			Changed	Changed	Changed
Sample Status				NORMAL	ABNORMAL	NORMAL

CONTAMINATION		method	limit/base	current	history1	history2
Fuel	WC Method	>4.0		<1.0	<1.0	<1.0
Water	WC Method	>0.1		NEG	NEG	NEG
Glycol	WC Method			NEG	NEG	NEG

WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>50	6	28	0
Chromium	ppm	ASTM D5185m	>4	<1	2	0
Nickel	ppm	ASTM D5185m	>2	<1	<1	0
Titanium	ppm	ASTM D5185m		19	13	0
Silver	ppm	ASTM D5185m	>5	0	0	0
Aluminum	ppm	ASTM D5185m	>12	4	7	<1
Lead	ppm	ASTM D5185m	>17	<1	15	0
Copper	ppm	ASTM D5185m	>70	0	4	<1
Tin	ppm	ASTM D5185m	>15	<1	1	0
Vanadium	ppm	ASTM D5185m		<1	<1	0
Cadmium	ppm	ASTM D5185m		0	0	0

ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		141	21	2
Barium	ppm	ASTM D5185m		0	0	0
Molybdenum	ppm	ASTM D5185m		53	116	54
Manganese	ppm	ASTM D5185m		<1	<1	<1
Magnesium	ppm	ASTM D5185m		993	640	911
Calcium	ppm	ASTM D5185m		2067	1429	1033
Phosphorus	ppm	ASTM D5185m	760	1064	665	1017
Zinc	ppm	ASTM D5185m	800	1190	817	1212
Sulfur	ppm	ASTM D5185m	3000	4804	2985	3031



CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6	9	4
Sodium	ppm	ASTM D5185m		7	▲ 364	2
Potassium	ppm	ASTM D5185m	>20	7	▲ 754	0

INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844		0.1	0.2	0.1
Nitration	Abs/cm	*ASTM D7624	>20	9.1	14.0	14.3
Sulfation	Abs/.1mm	*ASTM D7415	>30	18.8	23.5	21.3

FLUID DEGRADATION		method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	14.9	21.3	18.4
Base Number (BN)	mg KOH/g	ASTM D2896	10	7.5	6.6	9.7







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	14.6	13.8	15.4

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
 Sample No. : MW0047380
 Lab Number : 06121468
 Unique Number : 10930301
 Test Package : MAR 2

Received : 18 Mar 2024
 Tested : 19 Mar 2024
 Diagnosed : 21 Mar 2024 - Jonathan Hester

OSAGE MARINE
 7501 E DAVIS ST
 ST LOUIS, MO
 US 63111

Contact: MIKE KESSLER
 mike.kessler@osagemarine.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

T:
 F: