

OIL ANALYSIS REPORT

Sample Rating Trend

ISO

KAESER CSD 100 7683549 (S/N 1034)

Compressor

KAESER SIGMA (OEM) M-460 (--- GAL)

DIAGNOSIS

Recommendation

No corrective action is recommended at this time. The filter change at the time of sampling has been noted. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.


Contamination

There is a moderate amount of particulates present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

			Mar2022	Mar2024		
SAMPLE INFORM	NATION	method	limit/base	current	history1	history2
Sample Number		Client Info		KCPA014975	KCP43686	
Sample Date		Client Info		13 Mar 2024	11 Mar 2022	
Machine Age	hrs	Client Info		5691	1480	
Oil Age	hrs	Client Info		0	1480	
Oil Changed		Client Info		Not Changd	Changed	
Sample Status				ATTENTION	NORMAL	
WEAR METALS		method	limit/base		history1	history2
Iron		ASTM D5185m	>50		<1	
Chromium	ppm		>10	0 <1	0	
	ppm	ASTM D5185m				
Nickel	ppm	ASTM D5185m	>3	0	0	
Titanium	ppm	ASTM D5185m		0	0	
Silver	ppm	ASTM D5185m	>2	0	0	
Aluminum	ppm	ASTM D5185m	>10	<1	<1	
Lead	ppm	ASTM D5185m	>10	0	0	
Copper	ppm	ASTM D5185m	>50	5	1	
Tin	ppm	ASTM D5185m	>10	0	<1	
Vanadium	ppm	ASTM D5185m		0	0	
Cadmium	ppm	ASTM D5185m		0	0	
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0	
Barium	ppm	ASTM D5185m	90	6	0	
Molybdenum	ppm	ASTM D5185m	0	0	0	
Manganese	ppm	ASTM D5185m		<1	<1	
Magnesium	ppm	ASTM D5185m	100	49	79	
Calcium	ppm	ASTM D5185m	0	0	1	
Phosphorus	ppm	ASTM D5185m	0	0	6	
Zinc	ppm	ASTM D5185m	0	6	5	
Sulfur	ppm	ASTM D5185m	23500	25291	15601	
CONTAMINANTS	6	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	<1	1	
Sodium	ppm	ASTM D5185m		16	11	
Potassium	ppm	ASTM D5185m	>20	3	5	
Water	%	ASTM D6304	>0.05	0.016	0.019	
ppm Water	ppm	ASTM D6304	>500	163	197.7	
FLUID CLEANLIN	IESS	method	limit/base	current	history1	history2
Particles >4µm		ASTM D7647		10742	2632	
Particles >6µm		ASTM D7647	>1300	<u> </u>	544	
Particles >14μm		ASTM D7647	>80	160	35	
Particles >21µm		ASTM D7647		9 39	9	
Particles >38µm		ASTM D7647	>4	2	0	
Particles >71µm		ASTM D7647		0	0	
Oil Cleanliness		ISO 4406 (c)	>/17/13	2 1/18/14	16/12	
FLUID DEGRADA	TION_	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045	1.0	0.29	0.39	



60 Seve 55 Ab ()-050 ()-050 153 45

R

rma

Base Abnormal 40 Sev 35 1/22 Mar11

OIL ANALYSIS REPORT

	VISUAL		method	limit/base	current	history1	history2
	White Metal	scalar	*Visual	NONE	NONE	NONE	
	Yellow Metal	scalar	*Visual	NONE	NONE	NONE	
	Precipitate	scalar	*Visual	NONE	NONE	NONE	
	Silt	scalar	*Visual	NONE	NONE	NONE	
and and and an element and and an element of the days of the second second second second second second second s	Debris	scalar	*Visual	NONE	NONE	NONE	
	Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	
Marl 3/24	Appearance	scalar	*Visual	NORML	NORML	NORML	
N	Odor	scalar	*Visual	NORML	NORML	NORML	
	Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	
	Free Water	scalar	*Visual		NEG	NEG	
	FLUID PROPERT		method	limit/base		history1	history2
	Visc @ 40°C	cSt	ASTM D445	45	48.5	44.1	
	SAMPLE IMAGE	S	method	limit/base	current	history1	history2
Mar13/24	Color						no image
	Bottom						no image
	GRAPHS						
	Ferrous Alloys				Particle Coun	t	
	10 [iron]			491,5	20		T ²⁶
vc	6			122,8	80 -		-24
/ C				30,7	20		-22
14	2						
			<u> </u>	7,6	80		-20
	Mar11/22			Mar13/24 : (per 1 ml	20-		+18
	Mar			Mai les (pe	1	N	
	Non-ferrous Meta	s		10.	80-	\	-20 -18 -16 -14
	10 copper			t,	20-	~	+14
				um -		•	
					30-		-12
5	2				⁸ Bieresemal		10
C C 1							
μų.	11/22			Mar13/24	2-		
	Mar11.			Mar	0411 611	14μ 21μ	38µ 71µ
	Viscosity @ 40°C				Acid Number		<i>σσμ</i> τημ
	55 Severe			(B)+	20 Basermal		
				io C	96 - 9		
	(20 50 - Abnormal Base 45 - Abnormal			0.01(0) 0.01(0) 0.02(0	72		
	Abnormal			Juny .	⁴⁰ 24		
	35 Severe			- Acid	00		
5	/22						
C/ C	Marl1			Mar13/24	Mar11/22		
Sample No. Lab Number Unique Number			BLUE LINE TRANSFER IN 500 E JAMIE (SOUTH SAN FRANCISCO, C Hester US 940 Contact: G. COUT gcouto@ssfscavenger.co				

Contact/Location: G. COUTO - BLUSOUCA