




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Area
IRIG [6757440]
 Machine Id
IRIG-GN-0301 IRIG-GN-0301 COLD START GEN-MUD MODULE
 Component
Genset
 Fluid
CHEVRON DELO 400 MULTIGRADE 15W40 (13 QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

method	limit/base	current	history1	history2
Sample Number	Client Info	HLC0003032	HLC0001773	HLC0001083
Sample Date	Client Info	09 Mar 2024	22 Jun 2022	05 May 2021
Machine Age	hrs	3149	2640	2252
Oil Age	hrs	500	500	0
Oil Changed	Client Info	Changed	Changed	N/A
Sample Status		NORMAL	NORMAL	ABNORMAL

CONTAMINATION

method	limit/base	current	history1	history2
Fuel	WC Method >4.0	<1.0	<1.0	1.0
Water	WC Method >0.1	NEG	NEG	NEG
Glycol	WC Method	NEG	NEG	NEG

WEAR METALS

method	limit/base	current	history1	history2
Iron	ppm ASTM D5185m >50	25	37	6
Chromium	ppm ASTM D5185m >4	<1	<1	<1
Nickel	ppm ASTM D5185m >2	0	<1	0
Titanium	ppm ASTM D5185m	<1	<1	<1
Silver	ppm ASTM D5185m >5	0	0	<1
Aluminum	ppm ASTM D5185m >12	3	2	<1
Lead	ppm ASTM D5185m >17	0	<1	<1
Copper	ppm ASTM D5185m >70	<1	2	▲ 36
Tin	ppm ASTM D5185m >15	0	<1	<1
Antimony	ppm ASTM D5185m	---	---	0
Vanadium	ppm ASTM D5185m	0	0	0
Cadmium	ppm ASTM D5185m	0	0	0

ADDITIVES

method	limit/base	current	history1	history2
Boron	ppm ASTM D5185m 151	102	70	97
Barium	ppm ASTM D5185m 0.4	0	0	0
Molybdenum	ppm ASTM D5185m 250	14	4	<1
Manganese	ppm ASTM D5185m	0	<1	<1
Magnesium	ppm ASTM D5185m 0	760	835	665
Calcium	ppm ASTM D5185m 2046	1463	1584	1268
Phosphorus	ppm ASTM D5185m 1043	852	813	671
Zinc	ppm ASTM D5185m 943	905	920	749
Sulfur	ppm ASTM D5185m 5012	3348	3962	2388

CONTAMINANTS

method	limit/base	current	history1	history2
Silicon	ppm ASTM D5185m >25	4	6	3
Sodium	ppm ASTM D5185m	1	2	<1
Potassium	ppm ASTM D5185m >20	4	2	3

INFRA-RED



method	limit/base	current	history1	history2
Soot %	% *ASTM D7844	0.8	0.9	0.2
Nitration	Abs/cm *ASTM D7624 >20	8.7	9.0	8.2
Sulfation	Abs/.1mm *ASTM D7415 >30	20.2	20.4	19.5

FLUID DEGRADATION

method	limit/base	current	history1	history2
Oxidation	Abs/.1mm *ASTM D7414 >25	14.2	14.2	13.8
Base Number (BN)	mg KOH/g ASTM D2896 12.5	9.32	6.29	8.18







OIL ANALYSIS REPORT



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.1	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 100°C	cSt	ASTM D445	14.4	14.8	14.6 ▲ 12.2

GRAPHS



Certificate L2367

Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : HLC0003032
Lab Number : 06121749
Unique Number : 10930582
Test Package : IND 2

HILCORP EXPLORATION ALASKA - MILNE POINT
 1000 MILNE POINT RD
 PRUDOE BAY, AK
 US 99734
 Contact: Evan Reilly
 evan.reilly@hilcorp.com
 T: (907)670-3231
 F: x:

To discuss this sample report, contact Customer Service at 1-800-237-1369.

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)