

# **OIL ANALYSIS REPORT**

## Sample Rating Trend

## **NORMAL**



# CATERPILLAR D6T 8161 (S/N JML0276)

**Right Final Drive** 

{not provided} (--- QT

### Recommendation

Resample at the next service interval to monitor. Please specify the brand, type, and viscosity of the oil on your next sample.

All component wear rates are normal.

## Contamination

There is no indication of any contamination in the

### **Fluid Condition**


The condition of the oil is acceptable for the time in service.

S)  M2017									
SAMPLE INFOR	MATION	method	limit/base	current	history1	history2			
Sample Number		Client Info		WC0887943	WC0797744	WC0755247			
Sample Date		Client Info		12 Mar 2024	23 Jun 2023	23 Nov 2022			
Machine Age	hrs	Client Info		14106	13291	12908			
Oil Age	hrs	Client Info		815	328	454			
Oil Changed		Client Info		Changed	Changed	Changed			
Sample Status				NORMAL	NORMAL	NORMAL			
CONTAMINATIC	N	method	limit/base	current	history1	history2			
Water		WC Method	>0.2	NEG	NEG	NEG			
WEAR METALS		method	limit/base	current	history1	history2			
Iron	ppm	ASTM D5185m	>800	26	12	12			
Chromium	ppm	ASTM D5185m	>10	<1	<1	<1			
Nickel	ppm	ASTM D5185m	>5	0	<1	0			
Titanium	ppm	ASTM D5185m	>15	<1	<1	<1			
Silver	ppm	ASTM D5185m	>2	0	0	0			
Aluminum	ppm	ASTM D5185m	>75	2	0	1			
Lead	ppm	ASTM D5185m	>10	0	0	0			
Copper	ppm	ASTM D5185m	>75	<1	1	<1			
Tin	ppm	ASTM D5185m	>8	<1	<1	<1			
Vanadium	ppm	ASTM D5185m		0	0	0			
Cadmium	ppm	ASTM D5185m		0	0	0			
ADDITIVES		method	limit/base	current	history1	history2			
Boron	ppm	ASTM D5185m		155	150	106			
Barium	ppm	ASTM D5185m		0	0	0			
Molybdenum	ppm	ASTM D5185m		<1	0	<1			
Manganese	ppm	ASTM D5185m		<1	<1	<1			
Magnesium	ppm	ASTM D5185m		2	2	8			
Calcium	ppm	ASTM D5185m		94	466	1977			
Phosphorus	ppm	ASTM D5185m		324	418	953			
Zinc	ppm	ASTM D5185m		22	159	763			
Sulfur	ppm	ASTM D5185m		1849	2369	7386			
CONTAMINANT	S	method	limit/base	current	history1	history2			
Silicon	ppm	ASTM D5185m	>400	7	7	4			
Sodium	ppm	ASTM D5185m		0	0	<1			
Potassium	ppm	ASTM D5185m	>20	1	1	0			
VISUAL		method	limit/base	current	history1	history2			
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE			
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE			
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE			
Silt	scalar	*Visual	NONE	NONE	NONE	NONE			
Debris	scalar	*Visual	NONE	NONE	NONE	NONE			
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE			
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML			
Odor	scalar	*Visual	NORML	NORML	NORML	NORML			
<b>Emulsified Water</b>	scalar	*Visual	>0.2	NEG	NEG	NEG			
Free Water	scalar	*Visual		NEG	NEG	NEG			
\.10.E1\ David				Cant//	otion. MUZE MAN	ATT TOANIEM			

Contact/Location: MIKE WYATT - TRANEW





# **OIL ANALYSIS REPORT**




FLUID PROPERTIES		method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445		99.1	109	155
SAMPLE IMAGES		method	limit/base	current	history1	history2
Color				no image	no image	no image
Bottom				no image	no image	no image

## **GRAPHS**











Certificate L2367

Laboratory Sample No.

: WC0887943 Lab Number : 06122744 Unique Number : 10936895 Test Package : CONST

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 19 Mar 2024

**Tested** : 20 Mar 2024 Diagnosed

: 20 Mar 2024 - Wes Davis

Contact: MIKE WYATT mwyatt@traderconstruction.com

TRADER CONSTRUCTION CO.

T: (252)633-1399 F: (252)638-4871

PO DRAWER 1578

NEW BERN, NC

US 28563

To discuss this sample report, contact Customer Service at 1-800-237-1369. \* - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)