

## **OIL ANALYSIS REPORT**

Sample Rating Trend



Machine Id B995 Component Hydraulic System Fluid SHELL TELLUS 46 (--- QTS)

#### DIAGNOSIS

### Recommendation

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

## Wear

All component wear rates are normal.

## Contamination

There is no indication of any contamination in the oil.


#### Fluid Condition

The condition of the oil is acceptable for the time in service.

		Nov201	4 Dec2015	Dec2016 M	/lar2024	
SAMPLE INFORM	IATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0891835	WCI1102975	WCI16490
Sample Date		Client Info		18 Mar 2024	08 Dec 2016	11 Dec 2015
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	٨	method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	4	3	3
Chromium	ppm	ASTM D5185m	>20	2	3	3
Nickel	ppm	ASTM D5185m	>20	0	0	<1
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	<1	0
Lead	ppm	ASTM D5185m	>20	0	<1	<1
Copper	ppm	ASTM D5185m	>20	3	5	5
Tin	ppm	ASTM D5185m	>20	<1	0	<1
Antimony	ppm	ASTM D5185m	20		0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES	ppm		limit/base			
		method		current	history1	history2
Boron	ppm	ASTM D5185m	0.0	0	<1	0
Barium	ppm	ASTM D5185m	0	0	0	0
Molybdenum	ppm	ASTM D5185m	0	<1	<1	<1
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m	11	1	0	0
Calcium	ppm	ASTM D5185m	35	53	50	68
Phosphorus	ppm	ASTM D5185m	266	307	270	284
Zinc	ppm	ASTM D5185m	276	388	324	304
Sulfur	ppm	ASTM D5185m	1847	1019	1372	1199
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	2	<1	<1
Sodium	ppm	ASTM D5185m		0	0	0
Potassium	ppm	ASTM D5185m	>20	1	0	<1
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	LIGHT	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	: JERECAY COL	
				-		Page 1 of



# **OIL ANALYSIS REPORT**



	FLUID PROPERTI	ES method	limit/base curr	ent history1	history2
	Visc @ 40°C	cSt ASTM D445	46.99 <b>45.5</b>	45.64	45.41
	SAMPLE IMAGES	method	limit/base curr	ent history1	history2
19 49	Color		-		no image
Dec0/16 Mar10/24	Bottom				no image
	GRAPHS				
	Ferrous Alloys				
	4 3 2 1 0 4 1/1 10 5 1/1 10 0 10 10 10 10 10 10 10 10 10 10 10	Dec0/16	Mart 8/24		
	Non-ferrous Metals		War		
	udd 5 4 3 2 1 0 4 5 5 5 5 5 5 5 5	90	74		
	Viscosity @ 40°C	Dec8/16	Mar18/24		
	50 48 <b>Base</b> 46 46 44				
	42 40 38	9	24		
Laboratory Sample No. Lab Number Unique Number	: 10936938	Received : 19 Tested : 20	478, NC 27513 9 Mar 2024 0 Mar 2024 0 Mar 2024 - Wes Davis	Т	0 HESTER LI AZEWELL, TI US 3787
ficete L2367 Test Package discuss this sample report, Denotes test methods that rements of conformity to sp	contact Customer Servic are outside of the ISO 17	025 scope of accred	litation.	T:	EMY COLLIN s.sumiriko.cor (423)626-880 (423)626-206