

OIL ANALYSIS REPORT

Sample Rating Trend



Machine Id B1260 Component Hydraulic System Fluid SHELL TELLUS 46 (--- QTS)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor. NOTE: Please provide information regarding reservoir capacity, filter type and micron rating with next sample.

Wear

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The condition of the oil is acceptable for the time in service.

		Dec2014	Jan2016	Jan2017 M	//ar2024	
SAMPLE INFORM	1ATION	method	limit/base	current	history1	history2
Sample Number		Client Info		WC0891813	WCI1102492	WCI16477
Sample Date		Client Info		18 Mar 2024	18 Jan 2017	26 Jan 2016
Machine Age	hrs	Client Info		0	0	0
Oil Age	hrs	Client Info		0	0	0
Oil Changed		Client Info		N/A	N/A	N/A
Sample Status				NORMAL	NORMAL	NORMAL
CONTAMINATION	١	method	limit/base	current	history1	history2
Water		WC Method	>0.05	NEG	NEG	NEG
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>20	<1	<1	<1
Chromium	ppm	ASTM D5185m	>20	1	<1	<1
Nickel	ppm	ASTM D5185m	>20	0	0	0
Titanium	ppm	ASTM D5185m		<1	0	0
Silver	ppm	ASTM D5185m		0	0	0
Aluminum	ppm	ASTM D5185m	>20	2	0	1
Lead	ppm	ASTM D5185m	>20	<1	0	<1
Copper	ppm	ASTM D5185m	>20	6	10	10
Tin	ppm	ASTM D5185m	>20	<1	0	<1
Antimony	ppm	ASTM D5185m			0	0
Vanadium	ppm	ASTM D5185m		0	0	0
Cadmium	ppm	ASTM D5185m		0	0	0
ADDITIVES	ppm	method	limit/base	-	history1	history2
Boron	ppm	ASTM D5185m	0.0	0	0	<1
Barium	ppm	ASTM D5185m	0	0	0	<1
Molybdenum	ppm	ASTM D5185m	0	0	0	0
Manganese	ppm	ASTM D5185m		0	0	<1
Magnesium	ppm	ASTM D5185m	11	3	3	5
Calcium	ppm	ASTM D5185m	35	41	22	26
Phosphorus	ppm	ASTM D5185m	266	300	228	264
Zinc	ppm	ASTM D5185m	276	369	265	259
Sulfur	ppm	ASTM D5185m	1847	2226	3539	3827
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>15	1	1	1
Sodium	ppm	ASTM D5185m		0	0	2
Potassium	ppm	ASTM D5185m	>20	1	0	0
VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE	LIGHT
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG	NEG
Free Water	scalar	*Visual		NEG	: JEREKAY COL	LINSHERTRIA
						Page 1 of



OIL ANALYSIS REPORT



FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C cSt	ASTM D445	46.99	45.8	46.71	46.52
SAMPLE IMAGES	method	limit/base	current	history1	history2
Color					no image
Bottom					no image
GRAPHS					
Ferrous Alloys					
9 - iron 8 - normium 8 - normium					
7-					
6- E_5-					
4					
2					
	and a second sec	Crementer a			
Dec17/14 Jan26/16	Jan 18/17	Mar18/24			
Non-ferrous Metals	ø	2			
9 copper					
8tin 7 -					
6 - Ē 5 -					
4 +					
3					
- ************************************	The State of the second st	10000000000			
Dec17/14 Jan26/16	Jan 18/17	Mar18/24			
ے۔ Viscosity @ 40°C	2	W			
54 T					
52 - Abnormal 50 -					
48					
€ 46 - ਲ		_			
44					
40					
38 4 9		24			
Dec17/14 Jan26/16	Jan 18/17	Mar18/24			
: 06122816 Te : 10936967 Di	eceived : 19 ested : 20	v, NC 27513 9 Mar 2024 0 Mar 2024 1 Mar 2024 - W	'es Davis	Т	0 HESTER AZEWELL, US 378
: IND 1 contact Customer Service at	1-800-237-136	9.		Contact: JER	EMY COLLI s.sumiriko.co
are outside of the ISO 17025	scope of accred	litation.		T:	(423)626-88

To discuss this sample * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

Certificate L2367

F: (423)626-2065