


OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



EASG101493-4

Component

Diesel Engine

CHEVRON 15W40 (--- QTS)

	O.	10	0	
 ΙА	G١	M/	15	15

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.

Fluid Condition


The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

				Feb2024		
SAMPLE INFORM	MATION	method	limit/base	current	history1	history2
	I/TITON		IIIIIIIIII	WC0880972		1113101 y 2
Sample Number		Client Info		06 Feb 2024		
Sample Date Machine Age	hrs	Client Info		4382		
Oil Age	hrs	Client Info		1500		
Oil Changed	1115	Client Info		Changed		
Sample Status		Client inio		NORMAL		
CONTAMINATION	١	method	limit/base	current	history1	history2
Fuel		WC Method		<1.0		
Water		WC Method	>0.2	NEG		
Glycol		WC Method		NEG		
WEAR METALS		method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m	>100	1		
Chromium	ppm	ASTM D5185m	>20	0		
Nickel	ppm	ASTM D5185m	>4	0		
Titanium	ppm	ASTM D5185m		<1		
Silver	ppm	ASTM D5185m	>3	0		
Aluminum	ppm	ASTM D5185m	>20	3		
Lead	ppm	ASTM D5185m	>40	0		
Copper	ppm	ASTM D5185m	>330	<1		
Tin	ppm	ASTM D5185m	>15	0		
Vanadium	ppm	ASTM D5185m		<1		
Cadmium	ppm	ASTM D5185m		0		
ADDITIVES		method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m		357		
Barium	ppm	ASTM D5185m		0		
Molybdenum	ppm	ASTM D5185m		124		
Manganese	ppm	ASTM D5185m		<1		
Magnesium	ppm	ASTM D5185m		711		
Calcium	ppm	ASTM D5185m		1560		
Phosphorus	ppm	ASTM D5185m		770		
Zinc	ppm	ASTM D5185m		902		
Sulfur	ppm	ASTM D5185m		3167		
CONTAMINANTS		method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m	>25	6		
Sodium	ppm	ASTM D5185m	>50	<1		
Potassium	ppm	ASTM D5185m	>20	1		
INFRA-RED		method	limit/base	current	history1	history2
Soot %	%	*ASTM D7844	>3	0		
Nitration	Abs/cm	*ASTM D7624	>20	4.4		
Sulfation	Abs/.1mm	*ASTM D7415	>30	22.1		
FLUID DEGRADA	TION	method	limit/base	current	history1	history2
Oxidation	Abs/.1mm	*ASTM D7414	>25	15.0		
Base Number (BN)	mg KOH/g	ASTM D2896		9.7		
(- · ·)	0 3					



12


OIL ANALYSIS REPORT



VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERT	TIES	method	limit/base	current	history1	history2


14.0


Visc @	100°C
GRAF	PHS




cSt

ASTM D445 14.4











Certificate L2367

Laboratory Sample No.

: WC0880972 Lab Number : 06122909 Unique Number : 10937060 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received Tested

: 20 Mar 2024 : 20 Mar 2024 - Wes Davis Diagnosed

: 19 Mar 2024

DOLE FRESH FRUIT PO BOX 1689

GULFPORT, MS US 39502

Contact: JORDAN JOHNSTON

To discuss this sample report, contact Customer Service at 1-800-237-1369.

jordan.johnston@dole.com T:

* - Denotes test methods that are outside of the ISO 17025 scope of accreditation. Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)

F: (228)867-2970