

OIL ANALYSIS REPORT

DZGS103887

Component

Diesel Engine

CHEVRON 15W40 (--- QTS)

Sample Rating Trend

NORMAL

Recommendation

Resample at the next service interval to monitor. Please specify the component make and model with your next sample.

All component wear rates are normal.

Contamination

There is no indication of any contamination in the oil.


Fluid Condition

The BN result indicates that there is suitable alkalinity remaining in the oil. The condition of the oil is suitable for further service.

SAMPLE INFORM	MATION	method	limit/base	current	history1	history2				
	17111011	Client Info	mmbasc	WC0880943						
Sample Number		Client Info		31 Jan 2024						
Sample Date Machine Age	hrs	Client Info		12835						
Oil Age	hrs	Client Info		1500						
Oil Changed	1115	Client Info		Changed						
Sample Status		Client inio		NORMAL						
CONTAMINATION	١	method	limit/base	current	history1	history2				
Fuel		WC Method	>5	<1.0						
Water		WC Method	>0.2	NEG						
Glycol		WC Method		NEG						
WEAR METALS		method	limit/base	current	history1	history2				
Iron	ppm	ASTM D5185m	>100	8						
Chromium	ppm	ASTM D5185m	>20	<1						
Nickel	ppm	ASTM D5185m	>4	0						
Titanium	ppm	ASTM D5185m		<1						
Silver	ppm	ASTM D5185m	>3	0						
Aluminum	ppm	ASTM D5185m	>20	4						
Lead	ppm	ASTM D5185m	>40	0						
Copper	ppm	ASTM D5185m	>330	<1						
Tin	ppm	ASTM D5185m	>15	0						
Vanadium	ppm	ASTM D5185m		<1						
Cadmium	ppm	ASTM D5185m		0						
ADDITIVES		method	limit/base	current	history1	history2				
Boron	ppm	ASTM D5185m		303						
Barium	ppm	ASTM D5185m		0						
Molybdenum	ppm	ASTM D5185m		122						
Manganese	ppm	ASTM D5185m		<1						
Magnesium	ppm	ASTM D5185m		690						
Calcium	ppm	ASTM D5185m		1572						
Phosphorus	ppm	ASTM D5185m		732						
Zinc	ppm	ASTM D5185m		886						
Sulfur	ppm	ASTM D5185m		2971						
CONTAMINANTS		method	limit/base	current	history1	history2				
Silicon	ppm	ASTM D5185m	>25	5						
Sodium	ppm	ASTM D5185m	>50	31						
Potassium	ppm	ASTM D5185m	>20	<1						
INFRA-RED		method	limit/base	current	history1	history2				
Soot %	%	*ASTM D7844	>3	0.1						
Nitration	Abs/cm	*ASTM D7624	>20	7.9						
Sulfation	Abs/.1mm	*ASTM D7415	>30	23.0						
FLUID DEGRADA	TION	method	limit/base	current	history1	history2				
Oxidation	Abs/.1mm	*ASTM D7414	>25	18.9						
Base Number (BN)	mg KOH/g	ASTM D2896		8.6						
(- · ·)	99									




OIL ANALYSIS REPORT





VISUAL		method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE		
Yellow Metal	scalar	*Visual	NONE	NONE		
Precipitate	scalar	*Visual	NONE	NONE		
Silt	scalar	*Visual	NONE	NONE		
Debris	scalar	*Visual	NONE	NONE		
Sand/Dirt	scalar	*Visual	NONE	NONE		
Appearance	scalar	*Visual	NORML	NORML		
Odor	scalar	*Visual	NORML	NORML		
Emulsified Water	scalar	*Visual	>0.2	NEG		
Free Water	scalar	*Visual		NEG		
FLUID PROPERTIES		method	limit/base	current	history1	history2

FLUID PROPER	TIES	metnoa	ilmit/base	current	nistory i	nistory2
Visc @ 100°C	cSt	ASTM D445	14.4	12.7		



10 T		сор	per i							
8.1	*******									
6-										
4-										
2-										
0				 	******	 	 	 	 	
010	Jan3 I/24									







Laboratory Sample No.

: WC0880943 Lab Number : 06122916 Unique Number: 10937067 Test Package : FLEET

: WearCheck USA - 501 Madison Ave., Cary, NC 27513 Received : 19 Mar 2024 **Tested**

Diagnosed

: 20 Mar 2024 : 20 Mar 2024 - Wes Davis **DOLE FRESH FRUIT** PO BOX 1689 GULFPORT, MS US 39502

Contact: JORDAN JOHNSTON jordan.johnston@dole.com

To discuss this sample report, contact Customer Service at 1-800-237-1369. * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.

Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012) F: (228)867-2970

Contact/Location: JORDAN JOHNSTON - DOLGUL