




OIL ANALYSIS REPORT

Sample Rating Trend



ISO



Machine Id
SULLAIR AIR 1 SLA (S/N 13896KGC)

Component
Air Compressor

Fluid
USPI MAX FG AIR 46 (--- GAL)

DIAGNOSIS

Recommendation

We recommend you service the filters on this component. Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

There is a high amount of particulates present in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		USPM30494	USPM31336	USPM29030
Sample Date	Client Info		05 Mar 2024	14 Nov 2023	25 Jul 2023
Machine Age	hrs	Client Info	42122	42122	0
Oil Age	hrs	Client Info	0	0	0
Oil Changed	Client Info		N/A	N/A	N/A
Sample Status			ABNORMAL	ABNORMAL	ABNORMAL

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >50	0	0	<1
Chromium	ppm	ASTM D5185m >4	0	<1	0
Nickel	ppm	ASTM D5185m >4	0	0	0
Titanium	ppm	ASTM D5185m	0	0	0
Silver	ppm	ASTM D5185m	0	0	0
Aluminum	ppm	ASTM D5185m >10	0	1	0
Lead	ppm	ASTM D5185m >20	0	0	0
Copper	ppm	ASTM D5185m >40	6	11	16
Tin	ppm	ASTM D5185m >5	<1	0	0
Vanadium	ppm	ASTM D5185m	0	0	<1
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m 0	0	0	0
Barium	ppm	ASTM D5185m 0	0	0	2
Molybdenum	ppm	ASTM D5185m 0	0	0	0
Manganese	ppm	ASTM D5185m	0	0	0
Magnesium	ppm	ASTM D5185m 0	0	<1	<1
Calcium	ppm	ASTM D5185m 0	0	1	<1
Phosphorus	ppm	ASTM D5185m 0	0	0	0
Zinc	ppm	ASTM D5185m 0	0	0	6
Sulfur	ppm	ASTM D5185m 0	0	0	32

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	0	<1	<1
Sodium	ppm	ASTM D5185m	0	0	0
Potassium	ppm	ASTM D5185m >20	0	<1	1
Water	%	ASTM D6304 >0.6	0.006	0.015	0.016
ppm Water	ppm	ASTM D6304 >6000	61	154	163.7

FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647	>10000	▲ 28648	● 17350	▲ 55079
Particles >6µm	ASTM D7647	>2500	▲ 13609	▲ 6195	▲ 19288
Particles >14µm	ASTM D7647	>320	▲ 2171	▲ 665	▲ 1560
Particles >21µm	ASTM D7647	>80	▲ 735	▲ 192	▲ 384
Particles >38µm	ASTM D7647	>20	▲ 43	8	14
Particles >71µm	ASTM D7647	>4	2	1	1
Oil Cleanliness	ISO 4406 (c)	>20/18/15	▲ 22/21/18	▲ 21/20/17	▲ 23/21/18


FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045 0.16	0.23	0.14	0.22




OIL ANALYSIS REPORT


Particle Trend




Water (KF)




Acid Number



Water (KF)




Viscosity @ 40°C



VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	NONE
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	NONE
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.6	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG


FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	45.8	48.0	47.4

SAMPLE IMAGES




GRAPHS


Ferrous Alloys




Non-ferrous Metals




Viscosity @ 40°C



Particle Count



Acid Number



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : USPM30494 **Received** : 19 Mar 2024
Lab Number : 06123137 **Tested** : 20 Mar 2024
Unique Number : 10937288 **Diagnosed** : 21 Mar 2024 - Doug Bogart
Test Package : IND 2

TYSON - AMARILLO-PRO
 AMARILLO, TX
 US
 Contact: SERVICE MANAGER

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)