




OIL ANALYSIS REPORT

Sample Rating Trend



NORMAL



Machine Id
KAESER ESD 300 5461382 (S/N 1162)

Component
Compressor

Fluid
KAESER SIGMA (OEM) S-460 (--- GAL)

DIAGNOSIS

Recommendation

Resample at the next service interval to monitor.

Wear

All component wear rates are normal.

Contamination

The amount and size of particulates present in the system are acceptable. There is no indication of any contamination in the oil.

Fluid Condition

The AN level is acceptable for this fluid. The condition of the oil is suitable for further service.

SAMPLE INFORMATION

	method	limit/base	current	history1	history2
Sample Number	Client Info		KCPA013265	KCPA010153	KCP33375
Sample Date	Client Info		06 Mar 2024	18 Dec 2023	16 Oct 2023
Machine Age	hrs	Client Info	70071	60000	68160
Oil Age	hrs	Client Info	2912	0	3500
Oil Changed	Client Info		Not Chngd	N/A	Not Chngd
Sample Status			NORMAL	ABNORMAL	ABNORMAL

WEAR METALS

	method	limit/base	current	history1	history2
Iron	ppm	ASTM D5185m >50	3	41	0
Chromium	ppm	ASTM D5185m >10	<1	0	0
Nickel	ppm	ASTM D5185m >3	0	0	0
Titanium	ppm	ASTM D5185m >3	0	0	0
Silver	ppm	ASTM D5185m >2	0	0	0
Aluminum	ppm	ASTM D5185m >10	<1	0	0
Lead	ppm	ASTM D5185m >10	0	0	0
Copper	ppm	ASTM D5185m >50	7	25	33
Tin	ppm	ASTM D5185m >10	0	0	0
Vanadium	ppm	ASTM D5185m	0	0	0
Cadmium	ppm	ASTM D5185m	0	0	0

ADDITIVES

	method	limit/base	current	history1	history2
Boron	ppm	ASTM D5185m	0	0	0
Barium	ppm	ASTM D5185m 90	42	0	0
Molybdenum	ppm	ASTM D5185m	3	0	0
Manganese	ppm	ASTM D5185m	<1	0	0
Magnesium	ppm	ASTM D5185m 90	62	0	0
Calcium	ppm	ASTM D5185m 2	2	0	0
Phosphorus	ppm	ASTM D5185m	<1	0	0
Zinc	ppm	ASTM D5185m	0	0	0
Sulfur	ppm	ASTM D5185m	21891	9678	10615

CONTAMINANTS

	method	limit/base	current	history1	history2
Silicon	ppm	ASTM D5185m >25	2	0	0
Sodium	ppm	ASTM D5185m	30	<1	1
Potassium	ppm	ASTM D5185m >20	9	0	0
Water	%	ASTM D6304 >0.05	0.015	0.00	0.010
ppm Water	ppm	ASTM D6304 >500	159	0	109






FLUID CLEANLINESS

	method	limit/base	current	history1	history2
Particles >4µm	ASTM D7647		4735	---	196636
Particles >6µm	ASTM D7647 >1300		880	---	▲ 79045
Particles >14µm	ASTM D7647 >80		65	---	▲ 6187
Particles >21µm	ASTM D7647 >20		25	---	▲ 1194
Particles >38µm	ASTM D7647 >4		3	---	● 9
Particles >71µm	ASTM D7647 >3		0	---	0
Oil Cleanliness	ISO 4406 (c) >--/17/13		19/17/13	---	▲ 25/23/20

FLUID DEGRADATION

	method	limit/base	current	history1	history2
Acid Number (AN)	mg KOH/g	ASTM D8045 0.4	0.46	0.36	0.35


OIL ANALYSIS REPORT








VISUAL	method	limit/base	current	history1	history2
White Metal	scalar	*Visual	NONE	NONE	MODER
Yellow Metal	scalar	*Visual	NONE	NONE	NONE
Precipitate	scalar	*Visual	NONE	NONE	NONE
Silt	scalar	*Visual	NONE	NONE	▲ MODER
Debris	scalar	*Visual	NONE	NONE	NONE
Sand/Dirt	scalar	*Visual	NONE	NONE	NONE
Appearance	scalar	*Visual	NORML	NORML	NORML
Odor	scalar	*Visual	NORML	NORML	NORML
Emulsified Water	scalar	*Visual	>0.05	NEG	NEG
Free Water	scalar	*Visual		NEG	NEG

FLUID PROPERTIES	method	limit/base	current	history1	history2
Visc @ 40°C	cSt	ASTM D445	46	45.4	44.8

SAMPLE IMAGES	method	limit/base	current	history1	history2
---------------	--------	------------	---------	----------	----------



GRAPHS



Laboratory : WearCheck USA - 501 Madison Ave., Cary, NC 27513
Sample No. : KCPA013265
Lab Number : 06123212
Unique Number : 10937363
Test Package : IND 2 (Additional Tests: KF, PrtCount)

AXIUM PLASTICS
 9005 SMITHS MILL RD
 NEW ALBANY, OH
 US 43054
 Contact: P. LONGIA
 plongia@axiumplastics.com

To discuss this sample report, contact Customer Service at 1-800-237-1369.
 * - Denotes test methods that are outside of the ISO 17025 scope of accreditation.
 Statements of conformity to specifications are based on the simple acceptance decision rule (JCGM 106:2012)